

DIRECT DYES FOR :




- TEXTILE

- PAPER

ATLARECT (DIRECT DYES)		Color index No.	Light Fastness	Washing Fastness	Rubbing Fastness	Dischargeability		
	3%					Acetate Reserve	Neutral	Alkaline
Chrysophenine G		Y 12	4-5	2	4-5	5	5	2
Orange S		Or 26	3	3	4	4-5	4	3
Congo Red		R 28	2	2	4-5	2-3	4	4
Scarlet 4BS		R 23	3	2	4	5	3-4	3-4
Red 12 B		R 31	2	3	4	4	4	4
Sky Blue 5B		B 15	2	3	4	5	5	5
Copper Blue 2 B		B 168	2	3	4	2	2	2
Turq Blue GL		B 86	7	2	4	4	4	3
Brown MR		Br 2	2	2	4-5	3	4	5
Black EX 150%		Blk 38	2	3	4-5	3	4	3
Fast Black G		Blk 19	2	3	4	3	4	3

HIGH FASTNESS DIRECT DYES FOR :

TEXTILE

ATLARUS (DIRECT FAST)		S D C Classification	Solubility (80°C 176°F g:1)	Fastness (Fixing treat)		Change in Shade by fixing treatment
	3%			Light	Washing (50°C 122°F)	
Yellow PG		B	50	5	4 4	4-5
Yellow RL		B	80	6-7	4-5 5	4
Orange 2GL		B	80	6-7	4-5 4-5	4
Scarlet F2G		B	20	4	5 4-5	4B
Red BWS		B	100	4	4-5 5	4-5
Rose FR		B	100	3	5 5	3-4B
Blue BRL 200%		B	50	5	4G 5	3G
Blue 4BL		B	50	7	4 4	4
Turq. Blue FBL		B	50	5	4 4	4
Brown GTL		B	80	5	4-5	5
Black VSF 600		B	80	5	5	4-5