



COAL CONCEPTS PROFICIENCY TESTING

GENERAL ANALYSIS SAMPLE

REPORT – ONE HUNDRED AND SEVENTY-FOUR

Revision 00

Final report

DATE ISSUED 30th APRIL 2026

PARTICIPANT

LABORATORY CODE: a

R BABOOLAL (SCHEME MANAGER)

SCHEME COORDINATOR: S MAMABOLO

Disclaimer: Opinions and interpretations expressed herein are outside the scope of SANAS accreditation
**Moisture in the analysis sample is not included in the SANAS schedule of accreditation as robust statistics cannot be applied.*
Chlorine, Fluorine, Quick ash, ASTM ash and ASTM Volatiles is not included in the scope of accreditation.

THINKING QUALITY, QUALITY THINKING

REGISTRATION NUMBER: 2006/149731/23 (RMB INDUSTRIAL STATIONERS cc t/a)

81 CERAMIC CURVE, ALTON, RICHARDS BAY 3900 | TEL: +27(0)35 751 2446 | CEL: +27(0)83 6500151 | FAX: 0862605793

E-MAIL: ravi@coalconcepts.co.za | labsup@coalconcepts.co.za

EXECUTIVE SUMMARY

1. Ninety-eight samples were sent to participants with 97 results submitted timeously.
2. The total number of outliers detected were as follows (dry base):
 - Volatile matter x 3
 - Calorific value x 4
 - Total Sulphur x 2
 - Phos x 1
 - Hydrogen x 1
 - ASTM Volatile matter x 1
3. Chlorine, Fluorine, ASTM Ash, ASTM Volatile Matter participants were insufficient to apply robust statistical calculations.
4. Trending for your laboratory is as follows:

TABLE OF CONTENTS

ITEM	PAGE NUMBER
Letter to participant	4
List of participants	5
Type of sample used	6
Preparation of sample	6
Homogeneity check	6
Stability check	7
ISO Ash data	8
ISO Ash z-score trend	9
Quick Ash data	10
Quick Ash trend	11
ISO Volatile matter data	12
ISO Volatile matter z-score trend	13
Calorific value data	14
Calorific value z-score trend	15
Total sulphur data	16
Total sulphur z-score trend	17
Phosphorous data and Z-Score trend	18
Carbon data / Hydrogen data / Nitrogen data	19
AFT data and z-scores	20
ASTM Ash, ASTM Volatile, Chlorine & Fluorine	21
Conclusion	22
Terms & Conditions	23

Dear Participant

RE: PROFICIENCY TESTING RESULTS FOR THE MONTH OF APRIL 2026

Thank you for your participation in the Coal Concepts proficiency testing scheme.

Your laboratory code is as per the cover page.

All results are totally confidential. Any results in **Bold, Italics and Underlined** are outliers. Where applicable, the most extreme outliers have been eliminated from calculations using the Grubbs estimate for outliers. Robust statistics has been applied where possible. Analysis results have been reported on air dry and dry base. The dry base results have been used to calculate the z-scores. The z-scores are calculated by subtracting the average from the participant result then dividing by the standard deviation. **Note: All decimals are carried in the z-score calculation and only rounded off at the end of the calculation.**

Please take note of the following:

1. Z-scores between -1 and +1 is deemed acceptable
2. Z-scores between -2 and -3 should serve as a warning that the analysis result could get worse
3. Z-scores between +2 and +3 should also serve as a warning that analysis results could get worse.
4. Z- scores lower than -3 and exceeding +3 should warrant an investigation
5. Compare your result to the robust average which will be the assigned value. The measurement of uncertainty (UoM) of the results is also stated.
6. Z-Score calculation : $z\ score = \frac{(Lab\ result - Average\ result)}{Standard\ Deviation}$
7. Measurement protocols (SANAS R80, ISO/IEC 17043:2023, clause 7.1.2); Analysis accredited parameters can be carried out using techniques as follows:

ISO Ash – ISO 1171

ISO Volatile matter – ISO 562

Calorific Value determinations – ISO 1928/ASTM D5865

Total Sulphur Determination – ISO 19579 / ASTM D4239

Phosphorus in Coal – BS 1016/ISO 622/ XRF

CHN – ISO 29541 /ASTM D5373

AFT – ISO 540

8. Five consecutive z-scores above the zero line is considered a positive bias and five consecutive z-scores below the zero line is considered a negative bias. Note that this is guideline/suggestion form Coal Concepts and your quality system requirements may differ.

The Coal Concepts scheme adheres to the requirements of ISO/IEC 17043 – Conformity assessment – General requirements for proficiency testing.

Statistical analysis has been carried out using ISO/IEC 13528-Statistical methods for use in proficiency testing by interlaboratory comparisons, including procedures used to statistically analyse data, establishment of any assigned value, standard deviation and its uncertainty.

Please find results attached together with Z-score trends.

Best Regards

R Baboolal

LIST OF PARTICIPANTS

Africoal	Matil Lab
Afisam Dudfield	Mfulawamanzi
Ağrı İbrahim Çeçen Üniversitesi	Mincoal Lab
AH Knight Bultfontein	Ministry of Energy and Mineral Resources - Kingdom of Jordan
AH Knight	Mitra SK Morocco
Anglo Greenside (Thungela)	Mitra SK Richards Bay
Anglo Landau	ML Coal
Aqua Specto	Moruple
ArcelorMittal VDP	Msobo Coal
Azuresky Pty LTd	MTA Genel Müdürlüğü
Best enough - Cordite	Nelson Mandela University
Best enough 2 Seam	Noko Analytical laboratories (Witbank)
Best enough Laboratory -Springs	Noko Ntshovelo
Best enough NCC	PSB Analytical Services Netherlands
Best enough Overlook Alpha	Profi Lab Doo
Bestech Zomhlaba Resource Mine -Delmas	Rafinerija Nafte Beograd AD
Botswana Power Corp - B Power Station	RC Inspection
Botswana Power Corporation - A Power Station	Richards Bay Minerals
Bureau Veritas Inspectorate Laboratories - Alton	Ronewa Lab
Bureau Veritas Inspectorate Laboratories - Middelburg	Ronewa Lab Gugulethu
BV Matola Laboratory	Ronewa Wescoal
BV Moatize	Ruvuma Coal (Pty) Ltd
BV Nacala	SA Labs Ihtuba – Khanye
Castle Peak Power Station	SA Labs Ihtuba – Middelburg
CCIC City Deep	Sappi
CCIC Richards Bay	SB Mining Solutions - Belfast
celiklerholding	Seriti Kriel Colliery
Coal Connect Lab Services	Seriti New Denmark
Coal Concepts Richards Bay Lab	Seriti New Vaal
Cotecna Lurco	Sibonisiwe Clewer
Cotecna Middelburg	Sibonisiwe Middelburg
Cotecna Mimosa	Sibonisiwe Ritvlei
Cotecna Nasonti	Siza Coal Services - Botswana
Cotecna Phola	Siza Coal Services - Kinross
CIGroup	Siza Labs sampling & Testing Pty Ltd Zambezi Gas & Coal Mine
Department of Energy Philippines	Siza Leeuwpn
Dicem	Siza Mgayo
Ensayos técnicos Labmin SRL-Peru	Siza Middelburg
Eskom Arnot	Siza Minerals Lab - Gaborone
Eskom Camden	Siza NBC
Eskom Duvha	Siza Sasol
Eskom Erid	Siza Umlalazi
Eskom Erid TGA	Siza WestCoal
Eskom Grootvlei	South 32 Khutala
Eskom Kendal	Turkey ELI
Eskom Kriel	UAS Areshomeng
Eskom Lethabo	UAS-Bankfontein
Eskom Majuba	UAS Botswana
Eskom Matimba	UAS Hendrina
Eskom Matla	UAS-Khashani
Eskom Medupi	UAS Main Lab
Eskom Tutuka	UAS Sasol SCS
Exxaro Matla	UAS Twistdraai
Fauji Fertilizer Bin Qasim Limited	UIS
General Directorate of Coal Enterprises of Turkey	Umlabu processing PTY Ltd
Geological Survey of Tanzania	Universal Geominerals Sdn Bhd - Malaysia
Geoscience	Vinca Institute - Serbia
Glencore Boshoeck	Vitrovian
Glencore Lion	Yatagan Termik
Glencore Wonderkop	Yildiz Labs - Turkey
Gölbaşı Kimya Laboratuvarı İşletme Müdürlüğü	Ykenerji
HighVeld Lab	
Hwange Colliery	
Idwala Lime	
Imbally (Pty) Ltd	
İZANLAB LABORATUVARLARI A.Ş.	
İZMİR KÖMÜR LABORATUVARI	
Jindal Kiepersol	
Jindal Mozambique	
Jugoinspekt Belgrade AD Serbia	
KELEBEK KİMYA ÇEVRE LABORATUVARLARI PETROL GIDA	
Laboratory for solid fuels-Mining Institute Belgrade	
Labrite Lab	
Labrite Zanrunix Laboratory	
Leon Testing Pakistan	
Mafube Coal	

1. TYPE OF SAMPLE USED

The coal used in this proficiency testing round was bituminous coal.

2. PREPARATION OF SAMPLE

Approximately 1000kg’s of coal with an approximate top size of 50mm was sourced. This was crushed to -4mm using a jaw crusher. The -4mm material was reduced to -212um using a cross-beat pulveriser. The 212 material was sieved using a 212um screen. Any +212um material was pulverised and sieved until all material passed through the 212-um sieve.
All the -212um material was then mixed in a mixing drum for 4 hours.

3. HOMOGENEITY CHECK

There were approximately 114 participants in this round, 10 portions of sample were randomly extracted. These were packaged in their final form i.e. in 200ml sample bottles. The bottles were labelled 1 to 10. The results were as follows:

SAMPLE NO.	TEST PORTION 1	TEST PORTION 2	sample av (Xt)	range (Wt)	range sqd
1	14,37	14,29	14,33	0,08	0,0064
2	14,37	14,26	14,32	0,11	0,0121
3	14,33	14,24	14,29	0,09	0,0081
4	14,22	14,29	14,26	0,07	0,0049
5	14,30	14,32	14,31	0,02	0,0004
6	14,33	14,24	14,29	0,09	0,0081
7	14,31	14,26	14,29	0,05	0,0025
8	14,25	14,36	14,31	0,11	0,0121
9	14,27	14,22	14,25	0,05	0,0025
10	14,32	14,12	14,22	0,20	0,0400
GENERAL AVERAGE			14,28		
STANDARD DEVIATION			0,034		
WITHIN SAMPLE STANDARD DEVIATION			0,070		
BETWEEN SAMPLE STANDARD DEVIATION			0,035		

The between sample standard deviation must be $\leq 0.3 \times \sigma$

(σ = std deviation for the proficiency assessment)

σ = 0.286 was used, which is the repeatability for ISO ash (Ash % > 10%)
Hence = 0.286 x 0.3 = 0.086

Since 0.035 < 0.086 the samples are homogenous.

4. STABILITY CHECK

Samples were retained for sales as reference material. Ten of them were randomly chosen for stability testing. In order for the proficiency testing samples to be declared stable the general average from the homogeneity check and that of the stability check the difference in the general average should not differ by more than 0.3 X precision.

This test has been carried out about a month after the samples were received by the participating laboratories.

SAMPLE NO.	TEST PORTION 1	TEST PORTION 2	sample av (Xt)	range (Wt)	range sqd
1	14,22	14,23	14,23	0,01	0,0001
2	14,29	14,26	14,28	0,03	0,0009
3	14,24	14,24	14,24	0,00	0,0000
4	14,18	14,31	14,25	0,13	0,0169
5	14,22	14,27	14,25	0,05	0,0025
6	14,32	14,18	14,25	0,14	0,0196
7	14,26	14,28	14,27	0,02	0,0004
8	14,25	14,40	14,33	0,15	0,0225
9	14,22	14,28	14,25	0,06	0,0036
10	14,25	14,27	14,26	0,02	0,0004
GENERAL AVERAGE			14,26		
STANDARD DEVIATION			0,027		
WITHIN SAMPLE STANDARD DEVIATION			0,058		
BETWEEN SAMPLE STANDARD DEVIATION			0,030		


(σ = 0.286 was used)

For this report 0.286 was used


Absolute value of (14.26– 14.28) = 0.020

Since 0.020 < 0.286 the proficiency testing samples were stable


COAL CONCEPTS - PROFICIENCY TESTING - APRIL 2026					
ANALYTICAL PARAMETER : ISO ASH (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY (%)	DRY BASE (%)	Z-SCORE (DRY BASE)
	1a	2,57	14,27	14,65	1,03
	3a	2,30	14,30	14,64	0,97
	6a	2,44	13,95	14,30	-1,07
	9a	2,40	14,40	14,75	1,68
	10a	2,89	14,04	14,46	-0,11
	12a	2,65	14,12	14,50	0,17
	13a	2,65	13,68	14,05	-2,55
	20a	3,20	13,80	14,26	-1,32
	23a	2,30	14,00	14,33	-0,88
	28a	2,53	14,00	14,36	-0,68
	33a	2,60	14,30	14,68	1,24
	35a	2,60	14,30	14,68	1,24
	36a	2,10	14,10	14,40	-0,44
	38a	2,60	14,60	14,99	3,10
	42a	2,50	14,00	14,36	-0,70
	49a	2,53	14,32	14,69	1,30
	58a	2,35	14,16	14,50	0,15
	59a	2,00	14,34	14,63	0,94
	66a	2,31	14,20	14,54	0,36
	74a	2,30	14,20	14,53	0,35
	76a	2,30	14,10	14,43	-0,26
	78a	1,78	14,09	14,35	-0,79
	79a	2,71	14,15	14,54	0,41
	80a	2,35	14,07	14,41	-0,41
	88a	2,40	14,40	14,75	1,68
	91a	2,20	14,10	14,42	-0,35
	95a	2,90	14,30	14,73	1,51
	96a	2,60	13,98	14,35	-0,74
	99a	2,55	14,21	14,58	0,64
	100a	2,00	14,16	14,45	-0,16
	106a	2,12	14,18	14,49	0,07
	110a	2,24	14,17	14,49	0,11
	112a	2,43	14,08	14,43	-0,27
	117a	2,50	14,20	14,56	0,53
	135a	2,52	14,06	14,42	-0,32
	143a	2,47	14,05	14,41	-0,42
	145a	2,15	14,05	14,36	-0,71
	151a	2,40	14,10	14,45	-0,18
	162a	2,35	13,90	14,23	-1,45
	166a	2,40	14,10	14,45	-0,18
	169a	1,61	14,19	14,42	-0,32
	184a	3,10	13,80	14,24	-1,41
	195a	2,64	14,02	14,40	-0,46
	201a	2,10	14,40	14,71	1,40
	220a	2,33	14,10	14,44	-0,24
	221a	2,50	13,90	14,26	-1,32
	224a	2,61	14,19	14,57	0,57
	225a	2,50	14,40	14,77	1,77
	230a	2,29	14,09	14,42	-0,34
	234a	2,75	13,90	14,29	-1,10
	239a	2,63	14,18	14,56	0,53
	256a	2,71	14,17	14,56	0,54
	259a	2,27	14,10	14,43	-0,29
	267a	2,56	13,95	14,32	-0,96
	269a	2,70	14,00	14,39	-0,53
	282a	2,18	14,00	14,31	-0,99
	284a	2,40	13,90	14,24	-1,41
	295a	2,53	14,25	14,62	0,87
	296a	2,42	13,88	14,22	-1,52
	299a	2,85	14,15	14,57	0,54
	302a	2,10	14,10	14,40	-0,44
	310a	2,50	14,00	14,36	-0,70
	312a	2,33	14,23	14,57	0,56
	315a	2,23	14,15	14,47	-0,02
	317a	2,35	14,10	14,44	-0,22
	318a	2,70	14,00	14,39	-0,53
	323a	2,75	14,02	14,42	-0,36
	325a	2,48	14,47	14,84	2,18
	326a	2,00	14,30	14,59	0,70
Number of results	-	69	69	69	-
OUTLIERS	-	-	0	0	-
AVERAGE	-	2,44	14,12	14,48	-
STD DEVIATION	-	-	0,17	0,17	-
MEDIAN	-	-	14,10	14,44	-
%RSD	-	-	1,18	1,15	-
ROBUST AVERAGE	-	-	14,12	14,47	-
ROBUST STD DEVIATION	-	-	0,18	0,17	-
UoM			0,03	0,03	-




COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : QUICK ASH (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY (%)	DRY BASE (%)	Z-SCORE (DRY BASE)
	3a	2,30	14,10	14,43	0,26
	9a	2,40	14,50	14,86	2,28
	13a	2,65	13,68	14,05	-1,55
	20a	3,20	13,60	14,05	-1,57
	23a	2,30	14,20	14,53	0,74
	35a	2,60	14,20	14,58	0,96
	36a	2,10	13,80	14,10	-1,35
	38a	2,60	14,70	15,09	3,40
	49a	2,53	13,96	14,32	-0,27
	50a	2,28	14,06	14,39	0,05
	59a	2,00	14,08	14,37	-0,05
	73a	2,88	14,03	14,45	0,32
	74a	2,30	14,20	14,53	0,74
	80a	2,35	14,14	14,48	0,49
	84a	2,55	13,83	14,19	-0,89
	91a	2,20	14,00	14,31	-0,30
	94a	2,50	14,10	14,46	0,40
	95a	2,90	14,20	14,62	1,17
	100a	2,00	13,96	14,24	-0,64
	112a	2,43	14,00	14,35	-0,14
	143a	2,47	14,05	14,41	0,13
	145a	2,15	14,00	14,31	-0,34
	162a	2,35	13,80	14,13	-1,17
	169a	1,61	14,12	14,35	-0,13
	171a	2,53	14,07	14,44	0,27
	176a	2,42	13,84	14,18	-0,93
	178a	1,90	14,20	14,48	0,46
	179a	2,60	13,90	14,27	-0,51
	184a	3,10	13,70	14,14	-1,15
	201a	2,10	14,40	14,71	1,58
	221a	2,50	14,00	14,36	-0,09
	224a	2,61	14,12	14,50	0,57
	230a	2,29	14,05	14,38	0,00
	231a	2,33	14,12	14,46	0,37
	234a	2,75	13,80	14,19	-0,90
	244a	2,42	14,00	14,35	-0,15
	257a	2,30	13,90	14,23	-0,72
	258a	2,60	13,80	14,17	-1,00
	259a	2,27	14,30	14,63	1,21
	267a	2,56	14,10	14,47	0,44
	269a	2,70	13,90	14,29	-0,44
	282a	2,18	13,70	14,01	-1,78
	283a	2,10	14,19	14,49	0,55
	284a	2,40	14,40	14,75	1,79
	287a	2,42	13,82	14,16	-1,03
	296a	2,42	13,84	14,18	-0,93
	302a	2,10	14,40	14,71	1,58
	303a	2,47	13,80	14,15	-1,09
	310a	2,50	14,20	14,56	0,89
	312a	2,33	14,14	14,48	0,47
	314a	2,70	13,70	14,08	-1,42
	315a	2,23	14,18	14,50	0,60
	317a	2,35	14,20	14,54	0,78
	318a	2,70	13,90	14,29	-0,44
	320a	2,32	14,02	14,35	-0,12
	323a	2,75	13,81	14,20	-0,85
	327a	2,42	13,90	14,24	-0,64
	329a	2,30	14,00	14,33	-0,23
	330a	2,42	14,10	14,45	0,34
Number of results	-	59	59	59	-
OUTLIERS	-	-	0	0	-
AVERAGE	-	2,42	14,03	14,38	-
STD DEVIATION	-	-	0,21	0,21	-
MEDIAN			14,03	14,36	
%RSD	-	-	1,53	1,46	
ROBUST AVERAGE	-	-	14,03	14,37	
ROBUST STD DEVIATION	-	-	0,22	0,22	
UoM			0,04	0,04	




COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : ISO VOLATILE MATTER(%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	1a	2,57	18,70	19,19	0,14
	3a	2,30	19,00	19,45	0,72
	6a	2,44	18,67	19,14	0,02
	9a	2,40	19,00	19,47	0,77
	10a	2,89	18,03	18,57	-1,28
	12a	2,65	19,05	19,57	1,00
	13a	2,65	19,26	19,78	1,49
	<u>20a*</u>	3,20	<u>14,60</u>	<u>15,08</u>	<u>-9,19</u>
	23a	2,30	18,59	19,03	-0,23
	28a	2,53	18,27	18,74	-0,88
	33a	2,60	19,20	19,71	1,32
	35a	2,60	17,90	18,38	-1,71
	36a	2,10	18,40	18,79	-0,76
	38a	2,60	19,10	19,61	1,09
	42a	2,50	19,30	19,79	1,51
	49a	2,53	18,61	19,09	-0,08
	50a	2,28	19,10	19,55	0,95
	58a	2,35	18,44	18,88	-0,56
	59a	2,00	18,95	19,34	0,47
	66a	2,31	18,69	19,13	0,00
	73a	2,88	17,35	17,86	-2,87
	74a	2,30	18,80	19,24	0,26
	76a	2,30	17,40	17,81	-3,00
	78a	1,78	19,69	20,05	2,08
	79a	2,71	18,29	18,80	-0,75
	80a	2,35	18,88	19,33	0,47
	91a	2,20	19,90	20,35	2,77
	94a	2,50	18,30	18,77	-0,82
	95a	2,90	19,10	19,67	1,23
	96a	2,60	18,06	18,54	-1,33
	99a	2,55	18,32	18,80	-0,75
	100a	2,00	18,42	18,80	-0,76
	106a	2,12	18,51	18,91	-0,50
	110a	2,24	18,85	19,28	0,35
	112a	2,43	18,50	18,96	-0,38
	117a	2,50	18,50	18,97	-0,35
	135a	2,52	18,73	19,21	0,19
	143a	2,47	18,62	19,09	-0,09
	145a	2,15	18,60	19,01	-0,27
	151a	2,40	18,52	18,98	-0,35
162a	2,35	18,75	19,20	0,16	
166a	2,40	18,30	18,75	-0,86	
169a	1,61	19,29	19,61	1,08	
178a	1,90	18,78	19,14	0,03	
179a	2,60	18,50	18,99	-0,31	
184a	3,10	18,00	18,58	-1,26	
195a	2,64	18,58	19,08	-0,10	
201a	2,10	19,58	20,00	1,98	
220a	2,33	18,61	19,05	-0,17	
221a	2,50	18,40	18,87	-0,59	
224a	2,61	18,73	19,23	0,23	
225a	2,50	18,80	19,28	0,35	
230a	2,29	18,19	18,62	-1,17	
231a	2,33	18,58	19,02	-0,24	
234a	2,75	18,30	18,82	-0,71	
239a	2,63	18,34	18,84	-0,67	
256a	2,71	18,06	18,56	-1,29	
257a	2,30	18,64	19,08	-0,12	
258a	2,60	18,20	18,69	-1,01	
259a	2,27	18,47	18,90	-0,52	
267a	2,56	18,62	19,11	-0,05	
269a	2,70	18,90	19,42	0,67	
282a	2,18	19,00	19,42	0,67	
283a	2,10	18,56	18,96	-0,39	
284a	2,40	18,20	18,65	-1,09	
295a	2,53	18,32	18,80	-0,76	
296a	2,42	19,14	19,61	1,10	
299a	2,85	18,43	18,97	-0,36	
<u>302a*</u>	2,10	<u>20,60</u>	<u>21,04</u>	<u>4,34</u>	
303a	2,47	19,00	19,48	0,80	
310a	2,50	18,90	19,38	0,58	
312a	2,33	18,88	19,33	0,46	
314a	2,70	19,00	19,53	0,90	
315a	2,23	19,28	19,72	1,34	
317a	2,35	18,40	18,84	-0,65	
318a	2,70	18,80	19,32	0,44	
320a	2,32	19,10	19,55	0,96	
323a	2,75	18,60	19,13	0,00	
<u>325a*</u>	2,48	<u>16,94</u>	<u>17,37</u>	<u>-3,99</u>	
326a	2,00	19,07	19,46	0,75	
329a	2,30	19,00	19,45	0,72	
NUMBER OF RESULTS	-	81	81	81	-
OUTLIERS	-	-	3	3	-
AVERAGE	-	2,43	18,67	19,13	-
STD DEVIATION	-		0,45	0,44	-
MEDIAN			18,62	19,10	
%RSD	-	-	2,39	2,30	
ROBUST AVERAGE	-	-	18,67	19,13	-
ROBUST STD DEVIATION	-	-	0,47	0,46	-
UoM	-	-	0,07	0,07	-




COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : CALORIFIC VALUE (MJ/kg)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY (MJ/kg)	DRY BASE (MJ/kg)	Z-SCORE (DRY BASE)
	1a	2,57	28,31	29,06	-1,04
	3a	2,30	28,40	29,07	-0,98
	6a	2,44	28,60	29,32	0,26
	9a	2,40	28,86	29,57	1,53
	10a	2,89	28,64	29,49	1,14
	12a	2,65	28,40	29,17	-0,46
	<u>20a*</u>	3,20	<u>27,00</u>	<u>27,89</u>	<u>-6,87</u>
	23a	2,30	28,53	29,20	-0,31
	28a	2,53	28,45	29,19	-0,38
	33a	2,60	28,42	29,18	-0,43
	35a	2,60	28,62	29,38	0,60
	36a	2,10	28,36	28,97	-1,48
	38a	2,60	28,90	29,67	2,04
	42a	2,50	28,58	29,31	0,24
	49a	2,53	28,54	29,28	0,08
	50a	2,28	29,13	29,81	2,73
	66a	2,31	28,32	28,99	-1,37
	73a	2,88	28,44	29,28	0,10
	74a	2,30	28,39	29,06	-1,03
	76a	2,30	28,40	29,07	-0,98
	79a	2,71	28,51	29,30	0,20
	80a	2,35	28,35	29,03	-1,16
	84a	2,55	28,45	29,19	-0,35
	88a	2,40	28,73	29,44	0,86
	91a	2,20	28,94	29,59	1,64
	94a	2,50	28,43	29,16	-0,53
	95a	2,90	28,76	29,62	1,78
	96a	2,60	28,48	29,24	-0,12
	99a	2,55	28,49	29,24	-0,14
	<u>100a*</u>	2,00	<u>29,23</u>	29,83	2,82
	106a	2,12	28,62	29,24	-0,12
	110a	2,24	28,73	29,39	0,62
	112a	2,43	28,40	29,11	-0,78
	117a	2,50	28,46	29,19	-0,37
	135a	2,52	28,41	29,14	-0,60
	143a	2,47	28,37	29,09	-0,88
	145a	2,15	28,69	29,32	0,28
	151a	2,40	28,43	29,13	-0,68
	162a	2,35	28,92	29,62	1,76
	169a	1,61	28,60	29,07	-0,98
	171a	2,53	28,66	29,40	0,70
	176a	2,45	28,61	29,33	0,32
	178a	1,90	28,27	28,82	-2,24
	179a	2,60	28,52	29,28	0,09
	184a	3,10	28,70	29,62	1,77
	195a	2,64	28,66	29,44	0,87
	201a	2,10	28,25	28,86	-2,04
	209a	2,81	28,27	29,08	-0,90
	220a	2,33	28,47	29,15	-0,57
	<u>221a*</u>	2,50	<u>27,77</u>	<u>28,48</u>	<u>-3,92</u>
	224a	2,61	28,57	29,34	0,36
	225a	2,50	28,29	29,02	-1,24
	230a	2,29	28,55	29,22	-0,22
	231a	2,33	28,69	29,37	0,55
	233a	2,72	28,28	29,07	-0,97
	234a	2,75	28,69	29,50	1,19
	239a	2,63	28,33	29,10	-0,85
	244a	2,45	28,89	29,62	1,76
	256a	2,71	28,46	29,25	-0,06
	257a	2,30	28,54	29,21	-0,26
	258a	2,60	28,67	29,44	0,86
	259a	2,27	28,88	29,55	1,44
	269a	2,70	28,58	29,37	0,55
	282a	2,18	28,66	29,30	0,17
	283a	2,10	28,61	29,22	-0,20
	284a	2,40	28,71	29,42	0,76
	287a	2,45	28,35	29,06	-1,01
	295a	2,53	28,76	29,51	1,21
	296a	2,42	28,44	29,15	-0,59
	<u>299a*</u>	2,85	<u>23,67</u>	<u>24,36</u>	<u>-24,53</u>
	301a	2,59	28,48	29,24	-0,13
	302a	2,10	28,89	29,51	1,23
	303a	2,47	28,52	29,24	-0,11
	310a	2,50	28,56	29,29	0,14
	312a	2,33	28,63	29,31	0,25
	314a	2,70	28,65	29,45	0,91
	315a	2,23	28,56	29,21	-0,26
	316a	1,76	28,57	29,08	-0,91
	317a	2,35	28,71	29,40	0,69
	318a	2,70	28,33	29,12	-0,74
	320a	2,32	28,51	29,19	-0,38
	323a	2,75	28,71	29,52	1,29
	326a	2,00	28,50	29,08	-0,91
	327a	2,45	28,47	29,19	-0,40
	329a	2,30	28,40	29,07	-0,98
	330a	2,45	28,19	28,90	-1,83
NUMBER OF RESULTS	-	86	86	86	-
OUTLIERS	-	-	4	3	-
AVERAGE	-	2,45	28,55	29,26	-
STD DEVIATION	-	-	0,18	0,20	-
MEDIAN			28,54	29,24	
%RSD	-	-	0,65	0,68	
ROBUST AVERAGE	-	-	28,55	29,27	-
ROBUST STD DEVIATION	-	-	0,20	0,23	-
UoM	-	-	0,03	0,03	-



COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : TOTAL SULPHUR (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	1a	2,57	1,45	1,49	-1,70
	3a	2,30	1,73	1,77	1,30
	6a	2,44	1,59	1,63	-0,20
	9a	2,40	1,69	1,73	0,89
	10a	2,89	1,55	1,60	-0,55
	12a	2,65	1,59	1,63	-0,16
	20a*	3,20	1,16	1,20	-4,79
	23a	2,30	1,53	1,57	-0,88
	28a*	2,53	1,10	1,13	-5,53
	35a	2,60	1,48	1,52	-1,37
	36a	2,10	1,48	1,51	-1,45
	38a	2,60	1,70	1,75	1,03
	42a	2,50	1,69	1,73	0,91
	43a	2,42	1,70	1,74	1,00
	49a	2,53	1,54	1,58	-0,73
	50a	2,28	1,89	1,93	3,04
	58a	2,35	1,55	1,59	-0,65
	74a	2,30	1,69	1,73	0,87
	76a	2,30	1,58	1,62	-0,33
	78a	1,78	1,65	1,68	0,34
	79a	2,71	1,59	1,63	-0,15
	80a	2,35	1,76	1,80	1,64
	88a	2,40	1,71	1,75	1,10
	91a	2,20	1,80	1,84	2,05
	95a	2,90	1,69	1,74	0,98
	96a	2,60	1,68	1,72	0,82
	99a	2,55	1,64	1,68	0,37
	106a	2,12	1,63	1,67	0,18
	110a	2,24	1,60	1,64	-0,12
	112a	2,43	1,59	1,63	-0,20
	135a	2,52	1,52	1,56	-0,95
	143a	2,47	1,56	1,60	-0,52
	145a	2,15	1,58	1,61	-0,36
	151a	2,40	1,56	1,60	-0,53
	162a	2,35	1,59	1,63	-0,21
	169a	1,61	1,62	1,65	0,00
	178a	1,90	1,47	1,50	-1,59
	179a	2,60	1,54	1,58	-0,71
	184a	3,10	1,56	1,61	-0,41
	201a	2,10	1,55	1,58	-0,69
	221a	2,50	1,68	1,72	0,80
	224a	2,61	1,62	1,66	0,16
	225a	2,50	1,49	1,53	-1,28
	230a	2,29	1,61	1,65	0,00
	231a	2,33	1,58	1,62	-0,33
	233a	2,72	1,57	1,61	-0,37
	234a	2,75	1,61	1,66	0,08
	239a	2,63	1,56	1,60	-0,49
	257a	2,30	1,42	1,45	-2,07
	259a	2,27	1,63	1,67	0,21
	269a	2,70	1,69	1,74	0,94
	282a	2,18	1,59	1,63	-0,24
	283a	2,10	1,61	1,64	-0,04
	284a	2,40	1,48	1,52	-1,40
	287a	2,42	1,66	1,70	0,56
	295a	2,53	1,71	1,75	1,13
	296a	2,42	1,59	1,63	-0,20
	299a	2,85	1,72	1,77	1,30
	301a	2,59	1,54	1,58	-0,72
	302a	2,10	1,88	1,92	2,90
	303a	2,47	1,51	1,55	-1,06
	310a	2,50	1,60	1,64	-0,08
	312a	2,33	1,65	1,69	0,44
	314a	2,70	1,50	1,54	-1,13
	315a	2,23	1,55	1,59	-0,67
	316a	1,76	1,63	1,66	0,12
	317a	2,35	1,67	1,71	0,66
	320a	2,32	1,59	1,63	-0,22
	325a	2,48	1,62	1,66	0,12
	331a	2,66	1,50	1,54	-1,14
NUMBER OF RESULTS		70	70	70	-
OUTLIERS	-	-	2	2	-
AVERAGE	-	2,42	1,61	1,65	
MEDIAN		-	1,59	1,63	
STD DEVIATION	-	-	0,09	0,09	
%RSD	-	-	5,72	5,70	
ROBUST AVERAGE	-	-	1,61	1,65	-
ROBUST STD DEVIATION	-	-	0,10	0,10	-
UoM	-	-	0,02	0,02	-



COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER: PHOSPHOROUS IN COAL (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	1a	2,57	0,045	0,046	1,20
	9a	2,40	0,020	0,020	-1,73
	12a	2,65	0,043	0,044	0,97
	23a	2,30	0,032	0,033	-0,34
	38a	2,60	0,020	0,021	-1,73
	74a	2,30	0,023	0,024	-1,39
	78a	1,78	0,040	0,041	0,57
	112a	2,43	0,035	0,036	0,00
	114a	2,34	0,039	0,040	0,48
	145a	2,15	0,031	0,032	-0,46
	169a	1,61	0,034	0,035	-0,13
	177a	2,19	0,043	0,044	0,94
	234a	2,75	0,032	0,033	-0,32
	295a	2,53	0,042	0,043	0,84
	312a	2,33	0,044	0,045	1,07
	325a*	2,48	0,323	0,331	33,67
Number of results	-	16	16	16	-
OUTLIERS	-	-	1	1	-
AVERAGE	-	2,34	0,035	0,036	-
STD DEVIATION	-	-	0,009	0,009	-
MEDIAN		-	0,035	0,036	
ROBUST AVERAGE	-	-	0,035	0,036	
ROBUST STD DEVIATION	-	-	0,010	0,011	
UoM	-	-	0,003	0,004	



COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : TOTAL CARBON (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	12a	2,65	70,61	72,53	-0,14
	42a	2,50	68,40	70,15	-1,36
	43a	2,49	67,26	68,98	-1,96
	79a	2,71	70,01	71,96	-0,44
	177a	2,19	72,10	73,71	0,46
	224a	2,61	71,54	73,46	0,33
	234a	2,75	71,48	73,50	0,35
	295a	2,53	72,03	73,90	0,55
	299a	2,85	74,03	76,20	1,73
	312a	2,33	71,41	73,11	0,15
	316a	1,76	70,30	71,56	-0,64
	325a	2,48	72,85	74,70	0,96
Number of results	-	12	12	12	-
OUTLIERS	-	-	0	0	-
AVERAGE	-	2,49	71,00	72,81	-
MEDIAN	-	-	71,45	73,29	-
STD DEVIATION	-	-	1,86	1,96	-
%RSD	-	-	2,62	2,69	
ROBUST AVERAGE	-	-	-	-	
ROBUST STD DEVIATION	-	-	-	-	
UoM	-	-	-	-	

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER: HYDROGEN (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	1a	2,57	3,73	3,83	0,77
	12a	2,65	3,73	3,83	0,79
	42a	2,50	3,62	3,71	-0,19
	43a	2,55	3,70	3,80	0,51
	79a	2,71	3,50	3,60	-1,14
	177a	2,19	3,44	3,52	-1,80
	224a	2,61	3,66	3,76	0,19
	<u>234a*</u>	2,75	<u>4,14</u>	<u>4,26</u>	<u>4,30</u>
	295a	2,53	3,79	3,89	1,26
	312a	2,33	3,72	3,81	0,60
	331a	2,66	3,52	3,62	-0,98
Number of results		11	11	11	
OUTLIERS	-	-	1	1	-
AVERAGE	-	2,55	3,64	3,74	-
MEDIAN		-	3,68	3,78	-
STD DEVIATION	-	-	0,12	0,12	-
%RSD	-	-	3,22	3,25	
ROBUST AVERAGE	-	-	-	-	
ROBUST STD DEVIATION	-	-	-	-	
UoM	-	-	-	-	

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : NITROGEN (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	1a	2,57	1,93	1,98	0,14
	12a	2,65	1,89	1,94	-0,55
	42a	2,50	1,88	1,93	-0,78
	43a	2,53	1,83	1,88	-1,67
	79a	2,71	1,88	1,93	-0,71
	177a	2,19	1,97	2,01	0,72
	224a	2,61	1,93	1,98	0,16
	295a	2,53	1,95	2,00	0,49
	312a	2,33	1,94	1,99	0,24
	331a	2,66	2,03	2,09	1,98
Number of results		10	10	10	-
OUTLIERS	-	-	0	0	-
AVERAGE	-	2,53	1,92	1,97	-
MEDIAN		-	1,93	1,98	-
STD DEVIATION	-	-	0,06	0,06	-
%RSD	-	-	2,91	2,89	-
ROBUST AVERAGE	-	-	1,92	1,97	-
ROBUST STD DEVIATION	-	-	0,06	0,05	-
UoM	-	-	0,02	0,02	-

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER: ASH FUSION TEMPERATURES (oC)					
LAB ID	DEFORMATION	SOFTENING	HEMISPHERE	FLOW	
1a	1278	1298	1319	1353	
9a	1350	1370	1390	1420	
10a	1290	1320	1340	1370	
23a	1250	1270	1320	1400	
38a	1350	1370	1390	1410	
42a	1400	1420	1440	1470	
49a	1270	1310	1360	1410	
80a	1440	1480	1500	1500	
95a	1360	1390	1410	1430	
106a	1400	1440	1480	1500	
112a	1360	1390	1433	1460	
145a	1310	1330	1350	1370	
151a	1430	1490	1500	1500	
224a	1240	1270	1330	1380	
234a	1420	1440	1470	1500	
295a	1305	1340	1370	1410	
312a	1240	1260	1330	1440	
315a	1365	1408	1428	1473	
317a	1440	1450	1480	1500	
Number of results	19	19	19	19	
Outliers	0	0	0	0	
AVERAGE	1342	1371	1402	1437	
MEDIAN	1350	1370	1390	1430	
STDEV	69	72	64	51	

Z-SCORES				
LAB ID	DEFORMATION	SOFTENING	HEMISPHERE	FLOW
1a	-0,93	-1,01	-1,31	-1,66
9a	0,12	-0,01	-0,19	-0,33
10a	-0,76	-0,71	-0,98	-1,32
23a	-1,34	-1,40	-1,29	-0,73
38a	0,12	-0,01	-0,19	-0,53
42a	0,85	0,68	0,60	0,66
49a	-1,05	-0,85	-0,66	-0,53
80a	1,43	1,52	1,54	1,25
95a	0,26	0,27	0,12	-0,13
106a	0,85	0,96	1,23	1,25
112a	0,26	0,27	0,49	0,46
145a	-0,47	-0,57	-0,82	-1,32
151a	1,28	1,65	1,54	1,25
224a	-1,49	-1,40	-1,13	-1,12
234a	1,14	0,96	1,07	1,25
295a	-0,54	-0,43	-0,51	-0,53
312a	-1,49	-1,54	-1,13	0,07
315a	0,34	0,52	0,41	0,72
317a	1,43	1,10	1,23	1,25

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER: CHLORINE (ppm)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	12a	2,65	195	200	-
	177a	2,19	269	275	-
Number of results	-	2	2	2	-
OUTLIERS	-	-	-	-	-
AVERAGE	-	2,42	232	238	-
STD DEVIATION	-	-	-	-	-
MEDIAN	-	-	-	-	-

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER : FLUORINE (ppm)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY	DRY BASE	Z-SCORE (DRY BASE)
	12a	2,65	122	125	0,02
	169a	1,61	168	171	1,40
	177a	2,19	102	104	-0,62
	312a	2,33	96	98	-0,80
Number of results	-	4	4	4	-
OUTLIERS	-	-	0	0	-
AVERAGE	-	2,20	122	125	-
STD DEVIATION	-	-	33	33	-
MEDIAN	-	-	112	115	-

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER: ASTM ASH (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY (%)	DRY BASE (%)	Z-SCORE (DRY BASE)
	1a	2,57	14,31	14,69	0,41
	12a	2,65	14,24	14,63	0,05
	209a	2,81	13,95	14,35	-1,57
	224a	2,61	14,31	14,69	0,44
	233a	2,72	14,53	14,94	1,88
	239a	2,63	14,21	14,59	-0,14
	301a	2,59	14,34	14,72	0,61
	312a	2,33	14,34	14,68	0,38
	316a	1,76	14,17	14,42	-1,15
	331a	2,66	14,08	14,46	-0,91
Number of results	-	10	10	10	-
OUTLIERS	-	-	0	0	-
AVERAGE	-	2,53	14,25	14,62	-
STD DEVIATION	-	-	0,16	0,17	-
MEDIAN	-	-	14,28	14,65	
%RSD	a	-	1,12	1,16	-

COAL CONCEPTS - PROFICIENCY TESTING -APRIL 2026					
ANALYTICAL PARAMETER: ASTM VOLS (%)					
	LAB ID	MOISTURE IN ANALYSIS SAMPLE (%)	AIR DRY (%)	DRY BASE (%)	Z-SCORE (DRY BASE)
	1a	2,57	19,04	19,54	-1,19
	12a	2,65	19,09	19,61	-0,84
	209a	2,81	19,22	19,78	0,03
	224a	2,61	19,19	19,70	-0,34
	233a	2,72	19,37	19,91	0,74
	239a	2,63	19,03	19,54	-1,18
	301a	2,59	19,29	19,80	0,17
	312a	2,33	19,47	19,93	0,86
	316a	1,76	19,75	20,10	1,75
	<u>331a</u>	2,66	<u>22,01</u>	<u>22,61</u>	<u>14,86</u>
Number of results	-	10	10	10	-
OUTLIERS	-	-	1	1	-
AVERAGE	-	2,53	19,27	19,77	-
STD DEVIATION	-	-	0,23	0,19	-
MEDIAN	-	-	19,22	19,78	
%RSD	-	-	1,21	0,97	-

GENERAL CONCLUSIONS

1. The ISO Ash z-score trend is evenly distributed. The Robust average, Average and Median are similar. No outliers were detected.
2. The overall ISO volatile trend is evenly distributed. Three outliers were detected. These were due to analytical errors. An RSD of 2.30 % indicated a high precision of results received.
3. Calorific value trend is evenly distributed. Three outliers were detected. These seemed to be due to calibration errors. The Average, Median and Robust Average are the similar.
4. The sulphur z-score trend is evenly distributed. Two outliers were detected. The Average, Median and Robust Average are similar. A low precision of results received.
5. The phosphorous analysis results show a wide scatter, indicating significant data variability. One outlier were detected.
6. Generally acceptable results were obtained on Carbon, Hydrogen and Nitrogen. One Outlier was detected on hydrogen and one on.
7. Ash fusion: Generally acceptable results. No outlier was detected.

COAL CONCEPTS: Terms and Conditions

Return of results:

Laboratories participate in proficiency testing programs on the understanding that they will be sharing their results and information **anonymously** with other laboratories performing the same analysis. No return of results compromises the spirit of the programs, and reports will not be sent to laboratories unless they return results. Payment in full is required from all laboratories enrolling whether they return results or not.

Errors in Participant Proficiency Testing Results:

Proficiency testing reports should reflect the level of accuracy that a regular testing client would receive.

If a participant finds an error in their proficiency testing results, they may notify us in writing and change their submission **PRIOR** to the due date for return. Changes after this time will not be accepted.

Coal Concepts' reports result *as submitted* by participants.

On occasion, it seems as though participants have mixed up the samples or not processed the samples according to the instructions. Coal Concepts cannot make assumptions of this nature and change results 'to suit'. We also cannot compromise the integrity of the programs by suggesting to some participants that they should review their results prior to the due date. (This is unfair to other participants) It is the responsibility of the participants to check all aspects of the program, including sample identification, preparation, testing instructions, calculations and reporting of the results prior to results submission.

If samples are not in good condition on arrival to the participant laboratory, Coal Concepts must be notified in writing IMMEDIATELY, as often samples can be replaced in good time. Claims about samples received in bad condition will not be accepted after the report has been issued.

Late Enrolments and Late Results:

Late enrolment requests cannot always be accommodated, as sample manufacture must be scheduled well in advance to the shipping date of the program to allow all necessary quality assurance activities to be carried out.

Shipping of PT materials and evaluating test results from PTPs out of cycle with the mainstream programs is considerably time consuming and therefore costly.

In order not to disadvantage participants able to comply with time frames, Coal Concepts may charge a late fee in the following circumstances:

Requests that Coal concepts staff enters results on behalf of participants.

Requests to record results after the due date.

Requests for PTP participation that is out of cycle with the scheduled dates.

Shipping fees and Customs clearance:

Costs incurred for shipping samples and clearance of same through customs are the responsibility of the participating laboratory unless otherwise indicated.

Non-payment of fees:

Coal Concepts retains the right to withhold reports and/or test materials and services when invoices are outstanding.

Confidentiality of results:

All data and information received by Coal Concepts from its clients are considered confidential unless the client has given express permission to pass on information.

Definitions:

The dictionary definitions of "collusion" and "falsification" are as follows.

· *Collusion*: A secret agreement or cooperation for a fraudulent or deceitful purpose.

· *Falsification*: Deliberately changing something to be false. In proficiency testing terms, collusion is comparing data (and perhaps changing data) to fit in with a believed "correct" result. This is contrary to the spirit of proficiency testing programs, which are issued with the intention of providing an objective comparison of a laboratory's performance with others. Coal Concepts tries to minimise the occurrence of collusion by being aware that laboratories should be objective when they report their results and should therefore not know the intended results at the time, they are reporting to us.

Answers are not provided to clients until results have been submitted.

To prevent collusion and falsification our advice to clients is:

DON'T confer with others about PT samples or results.

DO accept the fact that everyone makes errors.

DON'T average the results or opinions of every person in the laboratory before selecting the answer to be submitted. Instead, use one of the answers AS SUBMITTED to you and take advantage of the Coal Concepts internal QA services and submit all answers generated by the technicians.

DO have confidence in your own results.

Proficiency Testing (PT) is a compulsory part of laboratory accreditation, but it is also an important tool for giving you confidence in your results. "Enhancing" your PT results with assistance from another participant cannot increase confidence in your laboratory's performance.

Coal concepts' testing staff are not told what the expected results are, nor what we are expecting.

We subject ALL results to analysis, even if they are different.

The staff have the right to check that the results we enter on their behalf are correctly transcribed.

Clients are always welcome to contact Coal Concepts to seek advice or information about collusion or falsification of data.

Policy for Participant Appeal of PT Performance Assessment:

If participants disagree with their performance assessment in a proficiency report, they should inform Coal Concepts in writing.

The response will include Coal Concepts interpretation of the outcome of the reassessment and an explanation of that outcome.

(For example, explanation of a calculation, or the rationale for the outcome of the evaluation.)

If a mistake has been made by Coal Concepts, it will be dealt with via Coal Concepts' non-conformance system.

Liability

In no event shall a party's liability to the other party for direct damages exceed an amount equal to the value of the amount for the PT Programme, under that specific month.

End of report