

May, 2013

3M™ Tape Primer 94

Product Description

3M™ Tape Primer 94 can be used to promote adhesion of 3M tapes to surfaces such polyethylene, polypropylene, ABS, PET/PBT blends, concrete, wood, glass, metal and painted metal surfaces.



3M™ Tape Primer 94

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	
Color	Clear light yellow – clear dark orange	
Net Weight	820 g/L	
Solids Content by Weight	6 %	
Flash Point	-20 °C	-4 °F
Coverage	14.7 m ² /L	600 sq ft/gal

Typical Uncured Physical Properties

Viscosity

Typical range is 1-10 cps (35 cps maximum) cP

Low VOC Alternates

Low VOC Alternates	g/l VOC	Substrates
3M™ Scotch-Weld™ Plastic Adhesive 2262 Thin 5 or 10 to 1 in acetone	196	Powder Paints
3M™ Scotch-Weld™ Plastic Adhesive 1099 Unthinned	0	Neoprene, Santoprene, EPDM

Note: 3M primer 94 contains greater than 250 g/l of volatile organic carbons (VOC). Less water, less exempt solvents. Please contact your local Air Quality Regulation to be sure this primer is compliant.

3M™ Tape Primer 94

Handling/Application Information

Application Techniques

Shake 3M Primer 94 well before using. Apply a thin uniform coating to the bonding surface using the minimum amount that will fully coat the surface. Allow 3M Primer 94 to dry thoroughly before applying tape. This is usually accomplished in 5 minutes at room temperature. Be sure the primed surface remains free from contaminants prior to applying the tape. Porous surfaces may require 2 applications of 3M Primer 94 for uniform coverage and good adhesion. Allow first application of primer to dry before applying the second coat. 3M Primer 94 may be applied with brush or swab. It can also be applied with a pressurized flow gun, knurled roller or other similar type of application equipment.

Clean up: 3M Primer 94 can be removed with acetone. Vigorous scrubbing may be required. Test in small area to insure acetone will not affect the substrate surface.

Note: Carefully read and follow manufacturer's precautions and directions for use when handling cleaning solvents.

Surface Preparation

The bonding surface must be relatively clean and dry. Contaminated surfaces should be cleaned with a 50/50 Isopropyl Alcohol and water mixture. A clean lint-free cloth should be used.

Storage and Shelf Life

When stored under proper conditions, product retains its performance and properties for 18 months from date of manufacture when stored in the original container at 60-80°F (15-27°C).

- Keep 3M™ Tape Primer 94 in the original container.
- Transfer only a small amount into a work vessel for use.
- Keep original container tightly sealed to avoid solvent evaporation.

Trademarks

3M and Scotch-Weld are trademarks of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~ /3M-Tape-Primer-94?N=5002385+3293194218&rt=rud

Table continued on next page

3M™ Tape Primer 94

References (continued)

Property	Values
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=94

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Tape Primer 94

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

3M™ Tape Primer 94



3M United States
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2021. All Rights Reserved.

The brands listed above are trademarks of 3M