

MODIFIED – CLEAR

7

THERMO RADIATA

Pinus radiata



WYCHWOOD
FOREST PRODUCTS

Clear 1 & Clear 2

Source: New Zealand

Appearance: Knot free

Condition: Thermally modified

Finish: Rough sawn

Density: 460 kg/m³

Size: Thickness 16–50mm, Width 100–250mm

Lengths: 3.0m / 3.6m / 4.2m / 5.1m, heavy 5.1m



Durability

CLASS 1*



Stability

EXCELLENT



Price

£££



Availability

EXCELLENT



Certification

FSC®

info@wychwoodfp.co.uk

01993 670967

THERMO AYOUS

Triplochiton scleroxylon



WYCHWOOD
FOREST PRODUCTS

FAS – Firsts and Seconds

Source: Cameroon

Appearance: Virtually knot free

Condition: Thermally modified

Finish: Rough sawn

Density: 360 kg/m³

Size: Thickness 16–80mm, Width 100–250mm

Lengths: 1.8m – 5.1m, average 4.2m



Durability

CLASS 1*



Stability

EXCELLENT



Price

£££



Availability

GOOD



Certification

OLB

THERMOWOOD® HEMLOCK

Tsuga heterophylla



Clears – 85/15

Source: Coastal, British Columbia, Canada

Appearance: Virtually knot free

Condition: Thermally modified

Finish: Rough sawn

Density: 450 kg/m³

Size: Thickness 7/8" – 2", Width 4" – 8"

Lengths: 6'–20', average 12'



Durability

CLASS 1*



Stability

EXCELLENT



Price

££££



Availability

VERY GOOD



Certification

PEFC

THERMOWOOD® RED OAK

Quercus rubra



FAS – Firsts and Seconds

Source: USA

Appearance: Virtually knot free

Condition: Thermally modified

Finish: Rough sawn

Density: 720 kg/m³

Size: Thickness 1", Width 5.5" – 8.5"

Lengths: 7'–16', average 12'



Durability

CLASS 1*



Stability

EXCELLENT



Price

££££



Availability

VERY GOOD



Certification

FSC®

THERMOWOOD® POPLAR

Liriodendron tulipifera



FAS – Firsts and Seconds

Source: USA

Appearance: Virtually knot free

Condition: Thermally modified

Finish: Rough sawn

Density: 460 kg/m³

Size: Thickness 1", Width 5.5" – 8.5"

Lengths: 6'-16', average 12'



Durability

CLASS 1*



Stability

EXCELLENT



Price

££££



Availability

VERY GOOD



Certification

FSC®

THERMOWOOD® ASH

Fraxinus americana



FAS – Firsts and Seconds

Source: USA

Appearance: Virtually knot free

Condition: Thermally modified

Finish: Rough sawn

Density: 620 kg/m³

Size: Thickness 1", Width 5.5" – 8.5"

Lengths: 6'-16', average 10'



Durability

CLASS 1*



Stability

EXCELLENT



Price

££££



Availability

LIMITED



Certification

FSC®

KEY



DURABILITY

- Class 1 – Very durable
- Class 2 – Durable
- Class 3 – Moderately durable
- Class 4 – Slightly durable

*Based on Use Class 3 application – above ground contact and subject to frequent wetting



STABILITY

- Poor – Prone to movement
- Good – Some initial movement expected
- Excellent – Minimal movement expected



PRICE

- ££ – Low
- £££ – Average
- ££££ – High
- £££££ – Very High



AVAILABILITY

- Limited – Restricted supply
- Good – Consistent supply
- Very good – Consistent high volume supply
- Excellent – Consistent & sustainable high volume supply



CERTIFICATION

- FSC® – Forest Stewardship Council® (FSC-C181063)
- PEFC – Programme for the Endorsement of Forest Certification
- OLB – Origine et Légimité des Bois