

WESTERN RED CEDAR Thuja plicata



No. 2 Clear & Better

Source: Coastal, British Columbia, Canada

Appearance: Virtually knot free

Condition: Green (KD on request)

Finish: Rough sawn

Density: 390 kg/m3

Size: Thickness 7/8" - 6", Width 4" - 12"

Lengths: 6'-20', average 12'



CLASS 2



EXCELLENT



£££££



LIMITED





WESTERN RED CEDAR Thuja plicata



No. 4 Clear / 85/15 Blended

Source: Coastal, British Columbia, Canada

Appearance: Predominantly knot free

Condition: Green (KD on request)

Finish: Rough sawn

Density: 390 kg/m3

Size: Thickness 7/8" - 6", Width 4" - 12"

Lengths: 6'-20', average 12'



CLASS 2



EXCELLENT



££££



LIMITED





DOUGLAS FIR



Pseudotsuga menziesii

Clears - 85/15

Source: Coastal, British Columbia, Canada

Appearance: Predominantly knot free

Condition: Kiln Dried

Finish: Rough sawn

Density: 530 kg/m3

Size: Thickness 7/8" - 4", Width 4" - 12"

Lengths: 6'-20', average 12'



CLASS 3



GOOD



£££



GOOD





WESTERN LARCH



Larix occidentalis

Clears - C & Better

Source: Coastal, British Columbia, Canada

Appearance: Predominantly knot free

Condition: Kiln Dried

Finish: Rough sawn

Density: 550 kg/m3

Size: Invoice 1" x 6" Net 1" x 5.5"

Lengths: 6'-20', average 12'



CLASS 3



GOOD



££££



LIMITED









DURABILITY

Class 1 - Very durable

Class 2 - Durable

Class 3 - Moderately durable

Class 4 - Slightly durable

*Based on Use Class 3 application - above ground contact and subject to frequent wetting



STABILITY

Poor - Prone to movement Good - Some initial movement expected Excellent - Minimal movement expected



PRICE

££ - Low £££ - Average ££££ - High £££££ - Very High



AVAILABILITY

Limited - Restricted supply Good - Consistent supply Very good - Consistent high volume volume supply Excellent - Consistent & sustainable high volume supply



CERTIFICATION

FSC® - Forest Stewardship Council® (FSC-C181063)
PEFC - Programme for the Endorsement of Forest Certification
OLB - Origine et Légalité des Bois