

# **GRAYWALL™ WATERPROOFING**

## PRODUCT SPECIFICATIONS

**COMPOSITION:** Polymer emulsion, applied membrane

**COLOR:** Gray

**DENSITY:** 6.8-7.8 lbs. / gallon

**MINIMUM TEMP FOR APPLICATION:** 15°F

**APPLICATION:** Airless spray

**APPLICATION RATE:** Poured wall or parged block: 30-40 sq ft/gallon

<b>PROPERTY</b>	<b>TEST METHODS</b>	<b>TEST RESULTS</b>
<b>Elongation</b>	ASTM D412 (die C)	1400+%
<b>Low-Temp Flexibility</b>	Bend around 0.5" mandrel	Flexible to -20°F
<b>Asphalt Content</b>	GPC	0.0%
<b>180 Degree Peel Adhesion</b>	Metal plate	18 lbs/inch
<b>Liquid Water Absorption</b>	ASTM D95	Less than 0.5%
<b>Resistance to Bacteria</b>	ASTM D42 99-83 (modified)	No attack
<b>Resistance to Degradation</b>	ASTM E-154 (soil prep.)	Excellent
<b>Resistance to Algae</b>	ASTM G2975 (modified)	No attack
<b>Resistance to Fungus</b>	ASTM D2020 (modified)	No attack