

Product parameters

Configuration outside inside	Visible light %		Solar radiation %		K-value W/ (m ² ·K)	Solar heat gain coefficient SHGC	Type of Low-E glass
	Transmittance τ_{vis}	Reflectance ρ_{vis}	Transmittance τ_e	Reflectance ρ_e			
5T+12A+5TL+V+5T	71.48	20.62	45.75	26.14	0.39	0.50	Single silver
	64.23	17.12	34.80	28.19	0.37	0.39	Double silver