

## Del Conca USA - Technical Characteristics

## SERIE WC, WOODCHIC collection.

ANSI A 137.1 - 2019 Table 10 : Porcelain Tile

Reference		Characteristics	Standard	Required values		DC USA Values:
		Nominal Size	ASTM C499	± 3%		Comply
Dimensional standard	e G	Caliber Range	ASTM C499	± 0.5%	± 0.08 in	Comply
	Calibrated	Warpage Edge	ASTM C485	± 0.5%	± 0.07 in	Comply
	Calik	Warpage Diagonal	ASTM C485	± 0.5%	± 0.07 in	Comply
		Wedging	ASTM C502	± 0.5%	± 0.08 in	Comply
		Nominal Size	ASTM C499	- 3%	+ 2%	Comply
	σ	Caliber Range	ASTM C499	± 0.25%	± 0.03 in	Comply
	Rectified	Warpage Edge	ASTM C485	± 0.4%	± 0.05 in	Comply
	Rec	Warpage Diagonal	ASTM C485	± 0.4%	± 0.07 in	Comply
		Wedging	ASTM C502	± 0.25%	± 0.03 in	Comply
		Thickness	ASTM C499	± 0.04	± 0.040 in	
		DEEP Abrasion	ASTM C1243	<175mm <sup>3</sup>		-40 mm <sup>3</sup>
		Bond Strength	ASTM C482	≥ 50 psi		Comply
ard		Water absorption	ASTM C373	Maximum 0.5%		~ 0.1%
Mechanical Standard		Thermal shock resistance	ASTM C484	Pass		Comply
nical		Chemical resistance	ASTM C650	550 Pass		Comply
chan		Stain resistance	ASTM C1378	Pass		Comply
Mee		Breaking Strength	ASTM C648	≥ 275 lbf		Comply
		Resistance to Freeze/Thaw cycling	ASTM C1026	As Reported		Comply
		MOHS		Declared value		Mohs ≥8

## DELCONCA USA

	Fire reaction - floor	EN 13823	Not Required			
	Fire reaction - wall	EN 13823	Not Required			
	VOC	No VOC				
US Require ments	Dynamic coefficient of Friction DCOF	ANSI A326.3- 2017 release 2019	Wet value ≥ 0.42	Nat	0.56	

Values reflect an average among test performed in our laboratory according to the standard requirements and/or trough third party laboratory.

Test are performed on actual production, first choice material. Values may vary between single individual production run.

Ceramica del Conca Technical team will be pleased to integrate and answer specific questions.