



Cafe







| Tile Formats | Mosaic | Bullnose |
|-----------------|--------|----------|
| | No | No |
| 8"x48" | | |
| Shade Variation | ▼ | |



High Variation

High shade and texture variation within each carton.



Technical Features

Dimensions | Surface flatness

| Warpage diagonal | mm | 1008.5±0.5% | ISO-10545-2 |
|--|--------------------|---|------------------------------|
| Warpage edge | mm | 901.8±0.5% | ISO-10545-2 |
| Physical properties | | | |
| Water absorption | % | 3 <wa≤6.0< td=""><td>ISO-10545-3</td></wa≤6.0<> | ISO-10545-3 |
| Breaking strength | kg/cm ² | ≥ 250 | ISO-10545-4 |
| Visible abrasion resistance | - | PEI (IV) | ISO-10545-7 |
| Thermal shock resistance | - | Resist | ISO-10545-9 |
| Crazing resistance | - | Resist | ISO-10545-11 |
| Resistance to freeze | - | Resist | ISO-10545-12 |
| Dynamic coefficient of friction (DCOF) | - | ≥ 0.42 | ANSI A 137-1, Section 9.6 |
| Chemical properties | | | |
| Chemical resistance | - | Resist ¹ | ISO-10545-13 |

| Stain resistance | - | Min Class 3 | ISO-10545-14 |
|------------------|---|-------------|--------------|

¹Avoid contact of the ceramic material with chemicals such as Muriatic Acid, Hydrofluoric Acid, Chlorine, Gasoline, Thinner, Diesel, cleaners that contain Potassium Hydroxide and other similar products, since the use of such substances can cause severe changes in the tile surface, altering its original appearance.