EMC Cement

Information Series



Embodied Carbon Ratings

For Low Carbon Concrete Innovation


EMC Volcanics: Embodied Carbon Ratings

Empowering California's push for low-carbon concrete innovation


Preliminary Information and Examples.

EMC Volcanics qualify as supplementary cementitious materials ("SCMs") to reduce the embodied energy and carbon tallies in both concretes and mortars. This document helps to show how. All examples below use the color boundaries and layout per the I.C.E.'s "Low Carbon Routemap" (here). In common with the Low Carbon Routemap, EPDs, and Calgreen's recent code innovations (here), the embodied carbon is expressed in kg·CO₂ per cubic meter (m³) of concrete, across LCA zones A1–A3 inclusively. In all treatments, I.C.E. data is used for the embodied CO₂ content of CEM I/Type 1 cement, more commonly known as Ordinary Portland Cement ("OPC"). This is rated at 915 kgs·CO₂/metric tonne ("MT"). This may be highly conservative. For example, Australia's EPiC database v.9 (here) rates OPC at 1,300 kgs·CO₂/MT. For EMC Volcanics, I.C.E.'s tally for aggregates is used (A1), plus a round-trip of 20 miles for the delivery of raw materials, using the U.S. truck average of 161.8g CO₂ per ton·mile (A2). Finally, zero carbon EMC Technology is low-energy and all-electric, for which we assume 100% renewable electricity for production purposes (A3).

The first three examples use the norms per EN 206's Table F (here). The next page then develops the same approach into a Caltrans setting using its 2023 standard specifications ("Caltrans-23"). In all stated cement dosages, the purely OPC equivalent is stated in red for easy visual comparison.



Example 1: An example from the Low Carbon Routemap. C28/35 is reinforced concrete intended for "moderate" exposure conditions. It requires a 28-day strength of 28 MPa (cylinder)/35 MPa (cube). The example uses CEM IIIA, which is a blended cement containing SCMs. Per EN-197, if slag is used, up to 65% of the OPC can be substituted. Here, slag is substituting 40% of the total cement's OPC dosage. At a total cement dosage of 300 kilos per m³, the embodied C0₂ is rated at 195kg/m³. Using 100% OPC at the same cement dosage, the CO₂ rating would be 275kg/m³ instead.



Example 2: At the same dosage and OPC substitution as Example 1, EMC Volcanics deliver a carbon improvement of ~30kg/m3 over Example 1.




Example 3: At the same dose as Examples 1 & 2, but increasing the OPC substitution to 70%, EMC Volcanics deliver a rating of only 84kg/m3!




Caltrans 2023 Specifications.

Caltrans-23 does not specify minimum strength-developments and it rarely requires minimum cement dosages. Two exceptions are freeze-thaw concretes and those "in corrosive environments", to comprise respective minimums of 590lbs/cu yd (890-1.02I) and 675lbs/cu yd (890-1.02H). Per its §90-1.01D(5)(a), there are two general rules for strength development. First, for concretes with a 28-day strength "greater than 3,600 psi, 42 days are allowed to attain the strength described". Second, 56 days "are allowed to meet the required strength", where the SCM ratio is above a formulaic ratio depending on the SCMs used. For 100% volcanics, this requirement is met at ~40% OPC substitution upwards. Further, per §90-1.01D(5)(b), there is no "pre-qualification" requirement if the 28-day strength requirement is less than 3,600 psi. These features favor low-carbon innovation.

The examples below follow Caltrans-23's requirements. Again, the pure-OPC dosed concrete is stated in red. As further insight, the energy used is set-out on both a per m³ and cu₂yd basis, together with the associated energy-savings when stacked against a pure-OPC counterpart. For OPC, we use I.C.E. data rated at 1,530 kWh/MT. This may be highly conservative. For example, Australia's latest EPiC database rates OPC at 11.8 GJ/MT (3,277 kWh/MT). By comparison, EMCs require about 120 kWh/MT, which have been increased to 150kWh/MT here in order to cover the energy requirement for raw material production, again using the I.C.E.'s figures for aggregates. Using California's stated metrics, the energy-savings are then expressed as a "days equivalent" measure of an average Californian household's and apartment's daily energy usage.



Examples 4 & 5: Both are for freeze-thaw environments, meeting Caltrans-23's minimum cement dosage of 590lbs/cu-yd. Volcanic SCMs cannot replace OPC by more than 36% (per Example 4). However, slags may replace OPC by 63% (per Example 5). EMC Volcanics can offer the same performance as slag. The two examples demonstrate the enhanced savings by allowing EMC Volcanics the same replacement-ceiling as slags.



Example 6: This is equivalent to a cement dosage of 275 kilos per m³, delivering a strength-class that, in context, accounts for 90-95% of all ready mix sales in the United Kingdom. At 70% OPC replacement, EMC Volcanics will easily deliver 3,600 psi strength by 56 days at this dosage, to also meet any 28-day pre-qualification need if adequately stipulated. As can be seen, EMC Volcanics deliver a carbon rating of only 77 kg/m3!

Prepared By EMC Cement BV

Produced 2023-09

All Rights Reserved.

For further information please feel free to contact us.

Copyright ©2023 EMC Cement BV. This document is for internal evaluation use only. Copying or transmission of this document whole or in part, for purposes beyond those as set out in the previous sentence is strictly prohibited, except with our express prior consent.

CemPozz and the three-leaf device whether not appearing in large print or with a "tm" or "®" trademark symbol, are trademarks of EMC Cement BV. The use or misuse of these trademarks or any other materials, except as may be permitted by us in writing, is hereby expressly prohibited and may be in violation of applicable law.

References to CemPozz products and services do not per se imply that EMC Cement BV (or any of its subsidiaries) is bound to offer or provide such products and services in every country throughout the World. Product specifications upon deliver may vary according to ultimate options chosen. Specifications of products are a matter of continual evaluation and evolution. We reserve the absolute right to amend vary modify our products in any manner as we deem fit without any obligation of prior notice.

Other company, product and service names may be trademarks or service marks of others.

Please be advised that EMC Cement BV enforces its intellectual property rights aggressively to the fullest extent permitted by law.

Unless stated otherwise, "tons" means U.S. short tons; "tonnes" means metric tons.

ΕN

EMC Cement B.V. Alvägen 33 SE - 97 332 Luleå Sweden

Tel: +46 705 498 892 E-mail: emcdev@telia.com

See: www.lowcarboncement.com





IMPORTANT NOTICE THIS IS NOT AN OFFERING MEMORANDUM. NOTHING HEREIN SHALL BE CONSTRUED AS AN OFFER TO SELL OR THE SOLICITATION OF AN OFFER TO BUY ANY SECURITIES OR OTHER INTERESTS IN OR THE SERVICES OF ANY AFFILIATE OF EMC OR TO IMPLY ANY TYPE OF FIDUCIARY RELATIONSHIP.

ALL INFORMATION HEREIN IS PROVIDED STRICTLY ON AN EX-GRATIA AND "AS IS" BASIS ONLY, BASED UPON ACTUAL OPERATING EXPERIENCE AND INFORMATION AS MAY BE PRESENTLY AVAILABLE TOGETHER WITH OUR OWN EVALUATIONS, INTERPRETATIONS, EXTRAPOLATIONS, ANALYSES, CALCULATIONS AS MAY BE PERFORMED FROM TIME TO TIME IN OUR ABSOLUTE DISCRETION.

ALTHOUGH REASONABLE CARE HAS BEEN TAKEN TO ENSURE THE ACCURACY OF THE CONTENTS OF THIS DOCUMENT, NO WARRANTIES OF ANY TYPE WHATSOEVER ARE GIVEN OR IMPLIED AS TO ITS ACCURACY.

