



Test Results

TEST RESULTS: ASTM C 1028 Slip Resistance Evaluation

SAMPLE	DRY SCOF	WET SCOF
"Alpaca - Unfinished"	0.8071	0.6545
"Alpaca - Honed"	0.7391	0.5719
"Cremino - Unfinished"	0.8314	0.7224
"Cremino Kello - Unfinished"	0.7780	0.6059
"Siena - Unfinished"	0.8945	0.6690

Current ADA regulations suggest that horizontal surfaces have a static coefficient of friction (SCOF) of 0.6 or greater and a ramped surface have a static coefficient of friction of 0.8 or greater. It should be noted that the larger the SCOF the more resistant the surface is to slipping.