

Rev. 08, Date 08.11.2023



MACLINE TMH

TEXTURED HIGH DENSITY POLYETHYLENE (HDPE) GEOMEMBRANES

MACLINE TMH is a high density polyethylene geomembrane (textured surface on one side) manufactured from maximum quality polyethylene resins, that comply with the most rigorous requirements established for their use. Geomembrane **MACLINE TMH** contains not less than 97% of pure polyethylene polymer and a balance not higher than 3% of carbon black, antioxidants and thermal stabilizers. The product does not contain plasticizers or fillers that could migrate over time. Textured HDPE improves the friction between the liner and the subgrade. Geomembrane **MACLINE TMH** are manufactured under permanent quality control and comply with national and international standards

SURFACE: SMOOTH/TEXTURED RAW MATERIAL CHARACTERISTICS							
Property	Unit	Test Method	Value				
Sheet density	g/cm ³	ASTM D-792	0.940				
Melt index	g/10min	ASTM D-1238, 190/2,16	1.0				
Carbon black content (2)	%	ASTM D-4218	2.0 - 3.0				
Carbon black dispersion	Category	ASTM D-5596	Cat.1/ Cat.2				
OIT—standard (avg.)	min	ASTM D-3895	100				

DURABILITY CHARACTERISTICS						
UV Resistance - %retained after 1600 hr HP OIT (min. avg.)	%	GRI-GM-11 ASTM D-5885	50			

GEOMEMBRANE PHYSICAL - MECHANICAL PROPERTIES		MACLINE TMH			
Tested Property	Unit	Test Method	100	150	200
Thickness (min. avg.)	mm	ASTM D-5199	1.00	1.50	2.00
Thickness (min.)	mm	ASTM D-5199	0.95	1.43	1.90
Aperity height (min. avg.)	mm	ASTM D-7466	0.40	0.40	0.40
Tensile properties (3): Tensile strength at yield Elongation at yield Tensile strength at break Elongation at break	kN/m % kN/m %	ASTM D-6693	15 12 13 100	22 12 16 100	29 12 21 100
Puncture resistance	N	ASTM D-4833	267	400	534
Tear Resistance (min. avg.)	N	ASTM D-1004	125	187	249
Dimensional stability (min. avg.)	%	ASTM D-1204	<u>+</u> 2.0		

NOTES

- (1) Correlation table is available for ASTM D-792 and ASTM D-1505. Both methods give the same result.
- (2) Correlation table is available for ASTM D-1603 and ASTM D-4218. Both methods give the same result.
- (3) Values are AVERAGE MINIMUM values.

For the optimisation and improvement process of the technical characteristics of the products, the producer reserves the factibility to modify standard and characteristics at the product without any warning. The information contained herein is to the best of our knowledge accurate, but since the circumstances and conditions in which it may be used are beyond our control, we do not accept any liability for any loss or damage, however arising, which results directly or indirectly from the use of such information nor do we offer any warranty or immunity against patent infringement

Maccaferri (Philippines), Inc.

- 11/F Asian Star Building, Asean Drive, Filinvest City, Alabang, Muntinlupa City 1781 Philippines
- T: + (63-2) 8889 0623
- E: info.ph@maccaferri.com www.maccaferri.com/ph