



GRENADE: SATIN PACK



11720 Main St, Suite 120
Fredericksburg, VA 22408
540-940-6698
admin@supplyndesign.com
www.supplyndesign.com

TECHNICAL DATA SHEET

Issue Date: 14-JULY-22

Revision Date: 14-JULY-22

Alt. Identifier: GR-SP

PRODUCT DESCRIPTION: SATIN ADDITIVE

BallistiX GRENADE SATIN PACK (GR-SP) additive is a proprietary flattening agent that is designed to be used with BallistiX SINGLE COMPONENT or COUNTERATTACK wherever a satin look is desired. Coating heavily glazed or high-gloss tile surfaces with minimal available anchor pattern (surface profile) is not recommended. Do not use with Anti-Skid Additive. **GR-SP additive should only be used on matte finish substrates such as Hard Tile, Quarry Tile, Terrazzo, etc.**

GR-SP is designed to be added to BallistiX SINGLE COMPONENT or COUNTERATTACK for installations over hard surfaces when a satin finish is desired. GR-SP does not affect coating performance. GR-SP keeps satin surfaces satin.

SURFACE PREPARATION

It is of utmost importance to ensure proper surface preparation. Be sure to read any and all available pre-treatment instructions for your chosen BallistiX product and thoroughly clean the surface with BallistiX ISOPROPYL 99.

MIXING INSTRUCTIONS

BallistiX GR-SP is pre-measured for your convenience:

1 Bottle GR-SP per 1 Quart BallistiX
4 Bottles GR-SP per 1 Gallon BallistiX

- Give BallistiX SINGLE COMPONENT or COUNTERATTACK a gentle shake (see specific product instructions).
- Shake the GR-SP bottle(s) vigorously by hand for at least 30 seconds.
- Add contents of the GR-SP bottle(s) into the BallistiX quart/gallon.
- Gently shake products until completely combined.

APPLICATION

To apply, use a metal or solvent-resistant paint pan with a recommended roller, or a pump-up sprayer to apply the coating, then back-roll with recommended roller. With either method, stir or agitate the coating just before filling the paint pan or pump-up sprayer to equally distribute the matte particles in the mixture. The sprayer should be shaken every 10 minutes through the application process to keep the particles in suspension.

- Use a 9", high-quality, 3/8" microfiber roller to distribute the coating evenly across the surface of the floor. Wet out the roller prior to application.
- Always finish by lightly pulling the roller towards you in long strokes. ***Any excessive downward pressure on the roller or dropping it into the starting position can leave lines or roller marks in the finished product.***
- For tack time, dry time and full cure time, refer to the SINGLE COMPONENT or COUNTERATTACK published Technical Data Sheets.



PRODUCT YIELD

BallistiX GR-SP additive with BallistiX products yields approximately 200+ ft² per quart or 800+ ft² per gallon, depending on application method, tile texture and grout porosity. Actual field conditions and application methods will dictate the final product yield.

POST-INSTALLATION CLEANING & MAINTENANCE

- Clean with water ONLY for the first 5 days after application.
- For most general, post-installation cleaning and maintenance situations, and in order to ensure the best cleaning results without damaging the newly installed BallistiX coating, use a neutral pH cleaner (no higher than 8 on the pH scale).
 - Prolonged use of the mop & bucket technique for cleaning will leave the floors dirty looking.
 - **Use Only Neutral pH (6-8) Cleaners and Disinfectants on BallistiX Coatings.**

RECOAT INFORMATION

- If a re-coat becomes necessary, hand sand or mechanically agitate the first installed coating with a fine grit sanding screen, nylon grit brush, or abrasive pad. Wet sanding minimizes dust generation.
- Remove sanding dust before product installation. Pick up residue with rinse and vacuum extraction equipment.
- If the re-coat 'pulls away' from the first coat, stop immediately, wipe up the fresh coating with BallistiX ISO 99 and continue sanding.