



EPDM Rubber Sheet Peroxide-Cured

Description: EPDM Sheet for ozone and sunlight resistance. Peroxide-cured compound to achieve even higher temperature ratings and improve ozone resistance over traditional sulfur-cured EPDM Sheet.

Durometer: 60 +/-5

Tensile: 1,800 psi

Elongation: 350%

Temperature: -40° F to + 212° F

Color: Black

Finish: Smooth

Specifications: ASTM D2000-M1-BA612

