



Ultra Light Filler Beads

Product Lineup - Select

Product Name	Avg Specific Gravity - g/cc	Avg Density - pounds/gallon	Avg Particle Size	Material Composition
Spex•Lite® 6503	0.011	0.1	3.2 mm	EPS
Spex•Lite® 6724	0.017	0.1	1.6 mm	EPS
Spex•Lite® MB 1085	0.017	0.1	70 - 100 µm	PVDC
Spex•Lite® 5524B	0.018	0.1	3.5 mm	EPP
Spex•Lite® MB 1755	0.025	0.2	145 - 165 µm	PVDC
Spex•Lite® 6807	0.030	0.3	1.1 mm	EPS
Spex•Lite® MB 4155	0.045	0.4	45 - 65 µm	PVDC
Spex•Lite® 5064	0.088	0.7	3 mm	EPP
Spex•Lite® 5125	0.160	1.3	2.5 mm	EPP
Spex•Lite® ELA 2125	0.360	3.0	250 - 500 µm	Glass
Spex•Lite® 3100	0.368	3.1	149 - 595 µm	PVC
Spex•Lite® HP 2555	0.460	3.9	5.5 µm	Calcined Alumina
Spex•Lite® ELA 4032	0.490	4.1	40 - 300 µm	Glass
Spex•Lite® 1018R	0.730	6.1	1.4 mm	PVC
Spex•Lite® HP 2520	0.828	6.9	2 µm	Calcined Alumina
Spex•Lite® HP 2560	0.924	7.7	6 µm	Calcined Alumina

Densities taken according to ASTM D1895.

Warranty: Spex•Lite warrants that this product, at the time of shipment, conforms to the specifications noted in the sections above. All other information provided herein is to be used as guidance only and there are no warranties relating to the information which extend beyond the description on the face hereof. ALL OTHER WARRANTIES, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED. Spex•Lite has a sole obligation and the sole and exclusive remedy under this limited warranty shall be the replacement of any defective product if justified by Spex•Lite. No warranty is given for any technical advice or recommendations provided by Spex•Lite. Buyer waives all claims under this limited warranty unless it has given written notice and proof of defect to Spex•Lite within 15 days of delivery.

440-462-1500
info@spexlite.com



29299 Clemens Rd #1-L
 Westlake, OH 44145 USA