

ABSTRACT

Specimen I. D. "Woodgrain 3D Laminate"

Test Standard: ASTM E84-13a TEST FOR SURFACE BURNING
CHARACTERISTICS OF BUILDING MATERIALS (UL
723, UBC 8-1, NFPA 255)

Test Date: August 27, 2014

Test Results:

FLAME SPREAD INDEX	15
SMOKE DEVELOPED INDEX	105

*According to the 2012 International Building Code Section 803.1.1,
the specimen meets the criteria for Class A criteria*

Fire Rating: Class A

Building Code Classification:

According to the 2012 International Building Code Section 803.1.1, interior and ceiling finish materials are classified based on the results from the ASTM E 84 Flame Spread Index and Smoke Developed Index values.

The 2012 International Building Code classifications are listed below.

Class A: Flame Spread Index 0-25; Smoke-Developed Index 0-450

Class B: Flame Spread Index 26-75; Smoke-Developed Index 0-450

Class C: Flame Spread Index 76-200; Smoke-Developed Index 0-450