



# DATA SHEET

## Black FFKM Rubber YG-FFKM

PHYSICAL PROPERTIES	REQUIREMENTS	TEST RESULTS
PRESS CURE @180°C X 1HR	***	
POST CURE @150°C X 4HR-->@200°C X 4HR-->@250°C X 16HR	***	
HARDNESS, SHORE A(1 SEC)	***	77.9
INTERNATIONAL HARDNESS	***	73.1
TENSILE STRENGTH, psi	***	2876
ELONGATION, %	***	197
MODULUS AT 100%	***	1542
SPECIFIC GRAVITY	***	2.001

### NOTE:

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.  
THIS COMPOUND EKRAZ 9635B CAN MEET ASTM D2000 PERFLUOROELASTOMER REQUIREMENT.



Yorkshire  
Gaskets Ltd



@gaskets247



CERTIFICATE NO. 14235  
ISO9001

The information given is based upon average values and is in no way intended as a warranty. The purchaser shall be responsible for determining the suitability of the product for any particular application.