



# DATA SHEET

## INTRODUCTION

Yorkshire Gaskets Grade YG - E is a general purpose commercial Non asbestos. Mostly recommended for industrial water supply and sewage in parameters shown below. The sheet is manufactured in hot alternating vulcanization process in accordance to high quality ISO 9001 standard procedures.

## Commercial Grade Non Asbestos YG- E

### MAXIMUM WORKING CONDITIONS

PEAK TEMPERATURE	220 °C	
TEMPERATURE UNDER CONTINUOUS OPERATION	150°C	
TEMPERATURE UNDER CONTINUOUS OPERATION WITH STEAM	130 °C	
MAX. PRESSURE UNDER CONTINUOUS OPERATION	MPa (bar) psi	4 (40 bar) 580 psi

### PHYSICAL AND CHEMICAL PROPERTIES

DENSITY +/- 5%	g/cm3	1,9	DIN28090-2
TRANSVERSE TENSILE STRENGTH MIN	MPa	4,0	DIN 52910
COMPRESSIBILITY, (TYPICAL VALUE)	%	6-16	ASTM F36
ELASTIC RECOVERY – MIN. 63280	%	50,0	ASTM F36
RESIDUAL STRESS 50MPa/16h/300°C	MPa	20,0	DIN 52913

### INCREASE IN THICKNESS

MODEL OIL NO. 3 150°C/5h (MAX)	%	6	ASTM F146
MODEL FUEL B 20°C/5h (MAX)	%	9	ASTM F146
DISTILLED WATER 100°C/4h MAX	%	5	ASTM F146



Yorkshire Gaskets Ltd



@gaskets247



CERTIFICATE NO. 14235  
ISO9001

The information given is based upon average values and is in no way intended as a warranty. The purchaser shall be responsible for determining the suitability of the product for any particular application.