

Made in the Kingdom of Bahrain

Omega 2150 Wood Primer

Finish: Flat
Type: Alkyd-based Primer - Wood



Product Description	
Type	Options (Code)
This is a premium quality alkyd wood primer. Formulated with faster drying stain blocking properties, this product can be used on multiple surfaces, penetrating and sealing bare wood for excellent adhesion. The product contains agents which inhibit the growth of mildew on the surface.	Wood Primer (2150)
Features	Benefits
A one-component alkyd-based system that offers ease of application and strong penetration to substrates. It is a flexible product that produces the ideal surface for subsequent paint finishes. It is an easy to apply product, fast drying to a tough flexible film with excellent flow and sanding properties.	• Penetrates and seals bare wood for excellent adhesion • Blocks stains from water, wood tannins and knots • One component • Easy to use
Typical Use	
Recommended as primer for wood substrates. Typical uses are doors, outdoor furniture, timber, weatherboards and window frames. Can be used on drywall, primed metal and cured masonry.	
Substrate	
Cement Plaster, Concrete, Block Work, Dry Wall, Wood and Ferrous Metals such as Steel and Iron. Substrate should have sufficient strength to receive the paint. Any defects in the substrate like surface undulations, cracks, pin holes, etc., should be rectified / filled before starting painting. The compatibility of any third-party filling material, if used, should be confirmed with Omega Paints® before application.	

Product Data

Colors

White

Packaging Size

1 USG , 5 USG

Solids Contents

55% +/- 2% volume theoretical

Volatile Organic Compounds (VOC)

350 - 375 g/l

VOC Comments

This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions

Application Method

Painting Tools

Roller: Use a suitable roller. Care must be taken to achieve the specified dry film thickness.

Brush: Use a suitable brush. Care must be taken to achieve the specified dry film thickness.

Spray: Use air spray

Guidelines for Airless Spray

Nozzle tip 1.4 to 1.6 mm

Pressure at Nozzle 2.5 bar

Distance from air compressor to filters is to be at least 10 m.

The product must be sprayed by professionals only.

Cleaning of Painting Tools

Omega 9011 Cleaning Thinner

Physical Characteristics

Film Thickness per Coat

Typical recommended range

Dry film thickness 30 - 55 µm

Wet film thickness 60 - 110 µm

Film thickness will vary and is calculated at average

Theoretical Spreading Rate (TSR)

7.0 - 14.0m² per liter

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

Specific Gravity	Flash Point	Viscosity
1.40 - 1.50 g/cm ³	40°C / 104°F	85-95 KU

Application Conditions

Stir thoroughly before and during use

To secure lasting adhesion all surfaces shall be clean, dry and free from any contamination

Surface temperature during application	Thinner	Dilution
The temperature of the substrate should be a minimum of 10°C and at least 3°C above the dew point of the air, measured in the vicinity of the substrate	Omega 9000 White Spirit	Maximum 20%

Moisture content must be below 17%

Good ventilation is usually required in confined areas to ensure proper drying

Drying Times

Substrate temperature	10°C	23°C	40°C
Surface (touch) dry	8 h	4 h	2 h
Walk-on-dry	12 h	6 h	3 h
Dry to over coat, minimum	24 h	12 h	6 h

Measured by Relative Humidity (RH) 50%

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and are generally related to air circulation, film thickness, and number of coats.

1. Recommended data given is, for reciting with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

Recommended Paint System

Primer

Omega 2150 Wood Primer x 1 coat

Filler

—

Topcoat

Omega Enamel series x 2 coats

Remarks

Other systems may be specified, depending on area of use and surface condition. Packaged contents with different batch numbers must be mixed together before use.

Directions of Use

Surface Preparation

Surface must be sound, clean, dry and free from dust, grease, oil, latencies, etc.

Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

Wood Surface

Surfaces with grease, oil, or other contamination is to be removed by detergents and fresh water cleaning. To secure lasting adhesion to the subsequent product all surfaces shall be clean and dry.

Plaster Condition

New plaster or masonry surfaces must cure for 30 days before applying base coat. Cured plaster should be hard, have a slight sheen; soft, porous or powdery plaster indicate improper cure.

Caution

Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Smooth planed clapboards or siding must be sanded thoroughly to break the mill glaze allowing proper penetration and adhesion

Applicators

The product is suitable for both professional and consumer application. The product must be sprayed by professionals only. The applicators shall be trained, experienced and have the capability and equipment to mix and apply the coatings correctly and according to Omega's technical documentation. Applicators shall use appropriate personal protection equipment when using this product. This guidelines is given based on the current knowledge of the product.

Difficult Substrates

Omega Paints® offers a number of specialty primers for use over difficult substrates. Your Omega Paints® representative can recommend the right problem-solving primer for your special needs.

Certifications

	Parameter	Test Method
1	Surface (touch) dry	Surface Drying
2	Opacity	BS EN 2814:2006
3	Scrub Resistance	ASTM D2486
4	Volatile Organic Compounds (VOC)	BS EN ISO 11890-2:2006
5	Solids by volume	ISO 3233
6	Flash Point	ISO 3679 Method 1
7	Gloss level (GU 60°C)	ISO 2813

Color: White

Copy of certificate and additional certificates and approvals available on request.

Storage and Handling

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf Life : 24 month(s)

Sealed and kept at normal temperature (not in direct sunlight)

Health and Safety

Apply under well-ventilated conditions. Do not breathe or inhale mist. When applying, wear air-mask and avoid skin contact. Spillage on skin should be immediately removed with suitable cleanser, soap, or water. Eyes should be well flushed with water and medical attention to be sought immediately. Please observe the environmental and precautionary notices displayed on the container.

Material Safety Data Sheet

A material safety data sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4

Handling and storage, refer to section 7

Transport information, refer to section 14

Regulatory information, refer to section 15

Disclaimer

The information in this document is given to the best of Omega's knowledge, based on laboratory testing, practical experience, and good faith.

Omega's products are manufactured to rigid standards, is considered as semi-finished goods and as such, products are often used under conditions beyond Omega's control. Omega cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements.

The company pursues a policy of continuous improvement in products, and as such, Omega reserves the right to change the given data without further notice. Users should always consult Omega for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English version will prevail.

Contact Omega's representative or visit www.omega-paints.com for more info.

Revision Date: **January 2024**