

Hardline Laboratory

TEST REPORT

Report No. : YA70237A/2025

Page : 1 of 2

Date : AUG. 14, 2025

OPTIQB AI TECHNOLOGY LIMITED

6F-7, Building B, 335 Ruiguang Rd., Neihu Dist., Taipei City 114, Taiwan

The following merchandise was submitted and identified by the applicant as:

Product Description: Qbarmour 3D Protective Film

Style/Item No.: iPhone 15plus/16plus

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: Pencil Hardness Test (According to customer's requested until 9H)

Test Method: Refer to ASTM D3363-20 Standard Test Method for film Hardness by Pencil Test

Test Result: ---See following sheet(s)---


Date of Receipt: JUL. 31, 2025

Testing Period: JUL. 31, 2025 ~ AUG. 14, 2025

Testing site:
7F, No. 6, Central 4th Road, Qianzhen Dist., Kaohsiung City, Taiwan

Signed for and on behalf of
SGS Taiwan Ltd.

Jon Wang
Team Leader



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TEST REPORTReport No. : YA70237A/2025
Page : 2 of 2Test load:1000 gThe variety of pencil hardness:6B – 5B – 4B – 3B – 2B – B – HB – F – H – 2H – 3H – 4H – 5H – 6H – 7H – 8H – 9H

Softer

Harder

Test Equipment:

Name	Brand	model
Pencil	MITSU-BISHI	uni

Lab Environmental Conditions:

Ambient temperature: (23 ± 2) °C

Relative humidity: (50 ± 5) %RH

Test Result:

Sample	Result
iPhone 15plus/16plus	9H


Note: The content of this report is invalid if it is not presented as the entire report.**– Picture(s) –**

Photo A: Appearance of the sample

---End of Report---