

Sponsor: Julie Zanatta Novo Textiles Co. 105-10 King Edward Street Coquitlam, BC V3K 4S8 CANADA

## Bacterial Filtration Efficiency (BFE) Final Report

Test Article: LOT 1591241652-FNT052520

Purchase Order: 06172020 Study Number: 1312024-S01 Study Received Date: 19 Jun 2020

Testing Facility: Nelson Laboratories, LLC

6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Test Procedure(s): Standard Test Protocol (STP) Number: STP0004 Rev 18

Deviation(s): None

**Summary:** The BFE test is performed to determine the filtration efficiency of test articles by comparing the bacterial counts downstream. A suspension of *Staphylococcus aureus* was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at 1.7 - 3.0 x  $10^3$  colony forming units (CFU) with a mean particle size (MPS) of  $3.0 \pm 0.3 \, \mu m$ . The aerosols were drawn through a six-stage, viable particle, Andersen sampler for collection. This test method complies with ASTM F2101-19 and EN 14683:2019, Annex B.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Inside BFE Test Area: ~40 cm<sup>2</sup>

BFE Flow Rate: 28.3 Liters per minute (L/min)

Conditioning Parameters: 85 ± 5% relative humidity (RH) and 21 ± 5°C for a minimum of 4 hours

Test Article Dimensions: ~172 mm x ~158 mm

Positive Control Average: 2.0 x 10<sup>3</sup> CFU

Negative Monitor Count: <1 CFU

MPS: 2.9 μm





Janelle Bentz electronically approved for

James Luskin

30 Jun 2020 19:57 (+00:00) Study Completion Date and Time

Study Director



## Results:

Test Article Number	Percent BFE (%)
1	>99.9 <sup>a</sup>
2	>99.9 <sup>a</sup>
3	>99.9
4	>99.9
5	>99.9 <sup>a</sup>

<sup>&</sup>lt;sup>a</sup> There were no detected colonies on any of the Andersen sampler plates for this test article.

The filtration efficiency percentages were calculated using the following equation:

$$\% BFE = \frac{C - T}{C} \times 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article
Note: The plate count total is available upon request



hcb