

3/10/2017

The Bucket Company Microbiological Analysis Report

Project No: 11770

Date Received: 2/25/2017 Date of Analysis: 3/7/2017

Subject: Bacteria Resistance Test in Hydrophobic or Polymeric Surfaces

Protocol

JIS Z 2801:2010, Japanese Industrial Standard Test for Antimicrobial Activity and Efficacy in Antimicrobial Products, was followed. Specifics of the test method applied to this project are described below.

Overview of Test Protocol

This test method is designed to evaluate (quantitatively) the antimicrobial effectiveness of agent(s) incorporated or bound into or onto mainly flat (two dimensional) hydrophobic or polymeric surfaces.

Specifics of the Test

Sample Identification

Lab ID	Sample ID			
11770-1	LDR Antimicrobial 0% (control)			
11770-2	LDR Antimicrobial 2%			
11770-3	LDR Antimicrobial 4%			

Test Organism

Escherichia coli ATCC# 8739

Test Protocol

Submitted samples were inoculated with 0.4 ml of a 0.2% nutrient broth seeded with a standardized culture of the test organism in triplicate. The inoculated samples were covered with an inert film and incubated at 36 ±2°C in a humidity chamber for 24 hours. Surviving microorganisms were recovered via elution of the broth inoculum from the test sample into neutralizing broth. Microbial counts of the samples were determined and the percent reduction of microorganisms (treated versus untreated samples at timepoint) was calculated.



3/10/2017

The Bucket Company Microbiological Analysis Report

Project No: 11770

Results

Tables 1 and 2 show the microbial resistance test results.

Conclusions

The Bucket Company sample LDR Antimicrobial 2% showed no antimicrobial activity against *Escherichia coli* after 24 hours incubation in the JIS Z 2801 test method with 0.00% reduction and an antimicrobial activity value of 0.00. Sample LDR Antimicrobial 4% showed >99.95% reduction and an antimicrobial activity value of >3.28. Percent reduction and antimicrobial activity were calculated against LDR Antimicrobial 0% control at the 24 hour timepoint.

Alicia Davis
Laboratory Manager

Silveria Cristo Microbiologist



3/10/2017

The Bucket Company Microbiological Analysis Report

Project No: <u>11770</u>

Test Method: JIS Z 2801:2010

Table 1. Recovered Organisms from controls at Time = 0 hours

Lab Identification	Escherichia coli ATCC# 8739 cells/cm ²					
	Replicate 1	Replicate 2	Replicate 3	Average		
11770-1 (control)	7.34 x 10 ³	8.59 x 10 ³	6.72 x 10 ³	7.55 x 10 ³		

Table 2. Recovered Organisms from controls and samples at Time = 24 hours

Lab Identification	Escherichia coli ATCC# 8739 cells/cm²				% Reduction	Antimicrobial Activity
	Replicate 1	Replicate 2	Replicate 3	Average		
11770-1 (control)	2.94 x 10 ⁵	2.17 x 10 ⁵	7.75 x 10 ³	1.73 x 10 ⁵	n/a	n/a
11770-2	2.97 x 10 ⁵	2.08 x 10 ⁵	2.53 x 10 ⁵	2.53 x 10 ⁵	0.00%	0.00
11770-3	2.77 x 10 ²	<0.625	<0.625	<92.8	>99.95%	>3.28