

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : MIROAD RUBBER INDUSTRIES SDN BHD
No 10-1D, Jalan Persiaran Teknologi Taman Teknologi
Johor 81400 Senai, Johor
Malaysia

Test Number : 23-003748
Issue Date : 15/09/2023
Print Date : 15/09/2023

Sample Description Clients Ref : "MIROAD EPDM Granules"
Softfall matting
Colour : Beige
End Use : Indoor/Outdoor Softfall Surfaces
Nominal Composition : EPDM Granules and Polyurethane Binder
Nominal Mass per Unit Area/Density : 950kg/m3
Nominal Thickness : 15mm



304668

66751

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : MIROAD RUBBER INDUSTRIES SDN BHD
No 10-1D, Jalan Persiaran Teknologi Taman Teknologi
Johor 81400 Senai, Johor
Malaysia

Test Number : 23-003748
Issue Date : 15/09/2023
Print Date : 15/09/2023

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 26-07-2023

Date Tested 30-08-2023

CHF Value	1	2	3	Mean
Non Directional	8.1	9.5	7.1	8.2 kW/m ²
HF-30 Value	1	2	3	Mean
Non Directional	9.8	-	8.8	- kW/m ²
Smoke Value	1	2	3	Mean
Non Directional	111	7	6	41 %min

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

No directional properties.

HF30 not reported as flame out time occurred before 30 minutes.

304668

66751

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR