

REPORT

Technical Report: (8521)021-0514

Page 1 of 3 JAN 26, 2021





TEST REPORT

MIROAD RUBBER INDUSTRIES SDN BHD LOT 6224, BATU 17 1/2, JALAN AIR HITAM, 81400 SENAI, JOHOR DARUL TAKZIM MALAYSIA **LAB LOCATION:** SHENZHEN (8521)021-0514

ATTN: MR KOO, MIN WERN roy@miroadrubber.com

koo@miroadrubber.com

DATE IN: JAN 22, 2021

MOD. LOG IN:

DATE OUT: JAN 26, 2021

REVISED DATE: / WORKING DAYS: 3

PAGE: 2 OF 3

	OVERALL RATING	
PASS FAIL DATA		Х

TESTING FOR GS MARK PAHS CONTENT

Sample Description:	EPDM	(MRD)								
Manufacturer:	MIROAD RUBBER INDUSTRIES SDN. BHD				P.O. No.:	/				
Buyer:	/			Style:	/					
Country of Origin:	MALAY	/SIA			Country of Destination:	GERN	/IAN	Y		
Color:	/				SKU Number:	/				
Re-test:	Yes:		No:	Х	Charge Vendor:	Yes:	Χ	N	o:	
Previous Report No.:	/	•	•	•		•		•		



EXECUTIVE SUMMARY:

Test content	Result/Rating		
GS mark PAHs content	Meet/Pass		

REMARK:

- 1. As per client's request, only the following test was conducted.
 - GS mark PAHs content
- 2. No protocol is enclosed for this report.

NOTE: If there are questions or concerns regarding above report, please contact the appropriate lab persons.

Technical questions & concerns: Peter Wan / Godfrey Yu

(+86)755-32980233 / 32980236 Peter.wan@bureauveritas.com Godfrey.yu@bureauveritas.com

General Enquiries: Nicole Zeng / Sharon Huang

(+86)755-86135624 / 86135512 Nicole.zeng@bureauveritas.com Sharon.huang@bureauveritas.com

BUREAU VERITAS SHENZHEN CO., LTD

BRIAN TAM

MANAGER - HARDLINES DIVISION

END OF REPORT

GS mark PAHs content

Sample ID	Color / Component	Location	Style
Α	Bright black rubber	EPDM(MRD)	All

		А
Test Parameter:	Limit	Result (mg/kg)
	(mg/kg)	
Naphthalene	1	ND
Phenanthrene	1	ND
Anthracene		ND
Fluoranthene		0.227
Pyrene		0.604
Benzo (a) anthracene	0.2	ND
Chrysen	0.2	ND
Benzo (b) fluoranthene	0.2	ND
Benzo (j) fluoranthene	0.2	ND
Benzo (k) fluoranthene	0.2	ND
Benzo (a) pyrene	0.2	ND
Benzo (e) pyrene	0.2	ND
Indeno (1,2,3-cd) pyrene	0.2	ND
Dibenzo (a,h) anthracene	0.2	ND
Benzo (g,h,j) perylene	0.2	ND
Total PAHs	1	0.831
Conclusion	/	PASS

ND = None Detected.