



Pane 1	PLANICLEAR (4 mm) Annealed Float PLANITHERM XN
Cavity 1	ARGON (90%) / AIR (10%) / 18 mm
Pane 2	PLANICLEAR (4 mm) Annealed Float
Cavity 2	ARGON (90%) / AIR (10%) / 18 mm
Pane 3	PLANITHERM XN PLANICLEAR (4 mm) Annealed Float

LA VENECIANA  
ALBERTO CIMAS

alberto.cimas@saint-gobain.com

**LUMINOUS FACTORS** CIE (15-2004)

Light transmission (TL %)	74,3 %	— VT
Outdoor reflection (RLe %)	14,4 %	
Indoor (RLi %)	14,4 %	

**SOLAR FACTORS** EN410 (2011-04)

Solar factor (g)	0,5423	— SHGC Value
Shading Coefficient (SC)	0,6234	

**COLOR RENDERING** CIE (15-2004)

Transmission (Ra)	96,6
Reflection (Ra)	94,0

**BURGLAR RESIST** EN356

Result :	NPD
----------	-----

**ENERGY FACTORS** EN410 (2011-04)

Transmission (Te)	47,7 %
Reflection (Ree)	32,3 %
Indoor (Rei)	32,3 %
Absorption (AE1)	11,4 %
Absorption (AE2)	3,8 %
Absorption (AE3)	4,8 %

**THERMAL TRANSMISSION** EN673 (2011-04)

Ug 0° related to vertical position	0,525 W/m².K
---------------------------------------	--------------

**MANUFACTURING SIZES** Ug=.092

Nominal thickness	48,0 mm
Weight	30,0 kg/m²

**PENDULUM RESISTANCE** EN12600

Result :	NPD
----------	-----

**ACOUSTICS** EN12758

Acoustic values according to EN 12758 and from notified body	Rw(C;Ctr) = 32(-1;-5) dB
--	--------------------------