


FLOCK HEAT TRANSFER VINYL



STRUCTURE



RECOMMENDED FABRICS

100% COTTON, 100% POLYESTER, POLY / COTTON BLENDS, LEATHER

SETTING & HOW TO USE



CUT

MIRROR IMAGE



BLADE

45 DEGREE



TEMPERATURE

150°C(302°F)
~160°C(320°F)



TIME

8-10 SECONDS



PRESSURE

MEDIUM



PEEL

HOT PEEL




WASH

WAIT AT LEAST 24
HOURS BEFORE FIRST
WASH



DETERGENT

MILD DETERGENT



THICKNESS

385-390 MICRONS
(WITHOUT PROTECTIVE
FILM)



HGWORLD



worldpaperweb@gmail.com



WORLDPAPEWEB



HGWORLD.US



<https://www.world-paper.com>



561-200-76-16