



POWER KABEL INC.

URD 35KV EPR/PVC @ 100% COPPER 1/3 NEUTRAL

APPLICATIONS & FEATURES

Underground primary residential and commercial distribution circuits. May be used in wet or dry locations, installed in underground ducts or direct burial. Low tension stripping compounds. Sealed conductor passes the production water penetration tests per ICEA--31-610 at 15 psi for 60 minutes. Strand Filled compound meets compatibility test requirements in accordance with ICEA-T-32-610

INDUSTRY COMPLIANCES

ICEA S-94-649 (Concentric Neutral Cables Rated 5 Through 46 kV.)

ASTM B8 (Concentric-Lay-Stranded Copper Conductors, Hard, Medium-Hard, or Soft.)

AEIC CS8 (Extruded Dielectric, Shielded Power Cables rated 5 kV - 46 kV.)

ASTM B231 (Concentric-Lay-Stranded Aluminum 1350 Conductors.)

CONSTRUCTION

CONDUCTORS:	Soft annealed uncoated copper Class B compressed or unilay compressed per ASTM B8
CONDUCTOR SHIELD:	Semi conducting cross-linked polyethylene (XLPE).
INSULATION:	Thermoset tree-retardant cross-linked polyethylene (TR-XLPE)
INSULATION SHIELD:	Semi conducting cross-linked polyethylene (XLPE).
CONCENTRIC NEUTRAL:	Soft annealed solid copper wires per ASTM B3, helically applied and uniformly spaced. Full or 1/3 Neutral.
BINDER TAPE:	A suitable polyester tape, as required
JACKET:	Overlying (sleeve) black polyvinyl chloride (PVC)

AWG	STRANDS	INSULATION THICKNESS (MILS)	OD OVER INSULATION (INCHES)	CONCENTRIC NEUTRAL (No X AWG)	JACKET THICKNESS (MILS)	OUTSIDE DIAMETER (INCHES)	POUNDS PER 1000 FT
1/0	19	345	1.10	9 x 14	80	1.50	1221
2/0	19	345	1.15	11 x 14	80	1.54	1371
3/0	19	345	1.20	14 X 14	80	1.59	1563
4/0	19	345	1.25	18 x 14	80	1.65	1801
250	37	345	1.31	13 X 12	110	1.80	2117
350	37	345	1.41	18 X 12	110	1.90	2629
500	37	345	1.54	17 X 10	110	2.10	3464
750	61	345	1.73	20 X 9	110	2.32	4701
1000	61	345	1.88	26 X 9	110	2.47	5872

All values are nominal and subject to correction.