



POWER KABEL INC.

URD 35KV TR-XLP @ 133% COPPER 1/3 NEUTRAL

APPLICATIONS & FEATURES

Underground primary residential and commercial distribution circuits. May be used in wet or dry locations, installed in underground ducts or direct burial. Low tension stripping compounds. Sealed conductor passes the production water penetration tests per ICEA--31-610 at 15 psi for 60 minutes. Strand Filled compound meets compatibility test requirements in accordance with ICEA-T-32-610

INDUSTRY COMPLIANCES

ICEA S-94-649 (Concentric Neutral Cables Rated 5 Through 46 kV.)

ICEA S-94-649 (Concentric Neutral Cables Rated 5 Through 46 kV.)

AEIC CS8 (Extruded Dielectric, Shielded Power Cables rated 5 kV - 46 kV.)

AEIC CS8 (Extruded Dielectric, Shielded Power Cables rated 5 kV - 46 kV.)

CONSTRUCTION

CONDUCTORS: Soft annealed uncoated copper Class B compressed or unilay compressed per ASTM B8
CONDUCTOR SHIELD: Semi conducting cross-linked polyethylene (XLPE).
INSULATION: Thermoset tree-retardant cross-linked polyethylene (TR-XLPE)
INSULATION SHIELD: Semi conducting cross-linked polyethylene (XLPE).
CONCENTRIC NEUTRAL: Soft annealed solid copper wires per ASTM B3, helically applied and uniformly spaced. Full or 1/3 Neutral.
BINDER TAPE: A suitable polyester tape, as required
JACKET: Overlying (sleeve) black polyvinyl chloride (PVC)

AWG	STRANDS	INSULATION THICKNESS (MILS)	OD OVER INSULATION (INCHES)	CONCENTRIC NEUTRAL (No X AWG)	JACKET THICKNESS (MILS)	OUTSIDE DIAMETER (INCHES)	POUNDS PER 1000 FT
1/0	19	420	1.25	9 X 14	80	1.65	1264
2/0	19	420	1.30	11 X 14	110	1.76	1517
3/0	19	420	1.35	14 X 14	110	1.81	1709
4/0	19	420	1.40	18 X 14	110	1.86	1948
250	37	420	1.46	13 X 12	110	1.95	2160
350	37	420	1.56	18 X 12	110	2.08	2716
500	37	420	1.69	17 X 10	110	2.26	3499
750	61	420	1.88	20 X 9	110	2.47	4728
1000	61	420	2.03	29 X 9	110	2.62	5892

All values are nominal and subject to correction.