

Scuff Tuff

Scuff Tuff is the only 100% acrylic modifier on the market today for use with Brewer Cote Resurfacer II and other Asphalt-Based Sealers. Scuff Tuff is specially formulated to increase chemical resistance and film strength, along with improving color and aggregate retention. Use Scuff Tuff where increased durability is needed in high wear areas, excellent for runways and taxi areas, along with all commercial and industrial properties. Also improves resistance to oils, fuels, grease, and water.

Coverage

Mix well before using, add after sealer has been diluted. Use 2 to 5 gal to every 100 gal of concentrated asphalt emulsion, depending on porosity.

Smooth to Medium Surfaces:

2 gal to every 100 gal of concentrated asphalt emulsion.

Rough to Excessively Rough Surfaces:

3 to 5 gal to every 100 gal of concentrated asphalt emulsion with 2 lbs additional Sand 60 mesh.

Method of Application

Diluted Brewer Cote Resurfacer II with a maximum of 20% water then add Scuff Tuff slowly while agitating. Add any additional sand (2 lbs per gal max) and mix for 10 mins.

Weather Limitations

For best results, do not apply on rainy days or when the temperature is expected to drop below 50° F during the next 24 hrs. On hot days, the pavement shall be pre-dampened with fog system. New asphalt should not be sealed until after exposed to a full summer heat cycle. Do not apply if rain is in the forecast for the next 24 hrs.

Drying Time 6 hrs. max at 70° F

Wash tools in water when wet 50% Relative Humidity use Bio-Degradable Solvent when dry

Clean Up

Color

Jet Black Finish

Packaging

5 gal Pails 55 gal Drums