

LIQUID BOOT® 500

SPRAY-APPLIED VAPOR BARRIER

DESCRIPTION

LIQUID BOOT® 500 is a seamless, spray-applied, water-based membrane containing no VOCs, which provides a barrier against vapor intrusion into structures. LIQUID BOOT® 500 spray-application directly to penetrations, footings, grade beams, pile caps and other irregular surfaces, provides for a fully-adhered vapor barrier system.

APPLICATIONS

LIQUID BOOT® 500 is used as an underslab vapor barrier, used to minimize vapor migration into buildings. LIQUID BOOT® 500 is ideal for methane migration control.

BENEFITS

- Can be installed more economically than LIQUID BOOT®, resulting in greater savings
- LIQUID BOOT® 500 is comprised of the same elements as LIQUID BOOT®
- Unique formulation provides superior protection from methane intrusion

INSTALLATION

Protect all adjacent areas not to receive vapor barrier. Ambient temperature shall be within

manufacturer's specifications. All plumbing, electrical, mechanical and structural items to be under or passing through the vapor barrier shall be secured in their proper positions and appropriately protected prior to membrane application. Vapor barrier shall be installed before placement of reinforcing steel.

Expansion joints must be filled with a conventional waterproof expansion joint material. Surface preparation shall be per manufacturer's specification. A minimum thickness of 60 dry mils, unless specified otherwise.

PACKAGING

LIQUID BOOT® 500 is available in the following packaging options:

- 55 Gallon Drum
- 275 Gallon Tote

EQUIPMENT

- COMPRESSOR: Minimum output of 155–185 cubic feet per minute (CFM)
- PUMPS: For "A" drum, an air-powered piston pump of 4:1 ratio (suggested model: Graco, 4:1 Bulldog). For "B" drum, an air-



powered diaphragm pump (0–100 psi)

- HOSES: For "A" drum, ½" wire hose with a solvent resistant core (for diesel cleaning flush), hose rated for 500 psi minimum. For "B" drum, a 3/8" fluid hose rated at only 300 psi may be used.
- SPRAY WAND: Only the spray wand sold by CETCO is approved for the application of LIQUID BOOT®.
- SPRAY TIPS: Replacement tips can be purchased separately from CETCO.

TESTING DATA

CHEMICAL & PHYSICAL PROPERTIES		
PROPERTY	TEST METHOD	RESULT
Elongation	ASTM D 412	> 500%
Bonded Seam Strength Tests	ASTM D 6392	Passed ¹
Methane Permeability	ASTM D 1434	None Detected
Microorganism Resistance (Soil Burial)	ASTM D4068-88	Passed ¹
Oil Resistance Test	ASTM D543-87	Passed ¹
Heat Aging	ASTM D4068-88	Passed ¹
Dead Load Seam Strength	City of Los Angeles	Passed ¹
Environmental Stress-Cracking	ASTM D1693-78	Passed ¹
Water Vapor Permeability	ASTM E96	0.22 perms
Adhesion to Concrete	ASTM C-836	Passed ¹
Hardness	ASTM C-836	Passed ¹
Hydrostatic Head Resistance (Tested at 20 psi)	ASTM D-751	Passed ¹

Notes:

¹ Passed City of Los Angeles methane barrier criteria

cetco@mineralstech.com | cetco.com | 800.527.9948

© 2017 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.cetco.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

