



PC RED INFIELD CONDITIONER

Typical Characteristics

Product Data

Product:

Pro's Choice Red Sports Field Conditioner

Manufacturer:

Oil-Dri Corporation of America
914 Curie Drive, Alpharetta, GA 30005
1-800-648-1166

Processing/Shipping Location:

Ripley, MS 38663

Description:

Natural mineral with a blend of Montmorillinite, illite, and amorphous silica. 40% minimum & 60% minimum amorphous silica. Material must be processed via rotary kiln operation at temperatures above 1200° Fahrenheit. Material must be screened and de-dusted.

Installation:

The following formula will be a guide for installing PC Red into your infield or root zone area. Infields should be conditioned at approximately 15% to 20% by volume. We recommend PC Red be rototilled 1-4 inches deep. Root zones should be approximately 20% by volume 4-6 inches deep depending on soils used.

Mineral Classification:

Fuller's Earth, Montmorillinite
(Calcium-Bentonite)

Color/Appearance:

Reddish Brown

Technical Data

Product Specifications:	Typical Analysis	Test Procedure
Foreign material	None	SE307.01.01
Bulk density, lbs/ft ³	35 lb/ft ³	DN001.01.01
pH	5.4	IN001.01.01
Free moisture %	0.6%	VL003.03.02
Hardness %	92.4%	HD001.02.01
Wet Slaking %	3%	HD005.01.01
Dust index	3.9	PS005.02.02
Grind Distribution	-6 / +40	PS001.02.01
Sieve analysis %		
+6 mesh	5%	
-6/+12 mesh	68%	
-12/+16 mesh	13%	
-16 mesh	14%	

Item Numbers:

A45201G40: 50 lb bags, 40 bags / pallet
A42201: Bulk Bag
A41201: Bulk Truck

