



# PC PROFESSIONAL INFIELD CONDITIONER

## Typical Characteristics

### Product Data

**Product:**

Pro's Choice Professional Sports Field Conditioner

**Manufacturer:**

Oil-Dri Corporation of America  
1-800-648-1166

**Processing/Shipping Location:**

1800 City Avenue North  
Ripley, MS 38663

**Description:**

Natural mineral with a blend of Montmorillinite, illite, and amorphous silica. 40% minimum & 60% minimum amorphous silica. Material must be processed via rotary kiln operation at temperatures above 1200° Fahrenheit. Material must be screened and de-dusted.

**Installation:**

The following formula will be a guide for installing PC Professional into your infield or root zone area. Infields should be conditioned at approximately 15% to 20% by volume. We recommend PC Professional be rototilled 1-2 inches deep. Root zones should be approximately 20% by volume 4-6 inches deep depending on soils used.

**Mineral Classification:**

Fuller's Earth, Montmorillinite  
(Calcium-Bentonite)

**Color/Appearance:**

Reddish Brown

### Technical Data

Product Specifications:	Typical Analysis	Test Procedure
Foreign material	None	SE307.01.01
Bulk density, lbs/ft <sup>3</sup>	35 lb/ft <sup>3</sup>	DN001.01.01
pH	8.9	IN001.01.01
Free moisture %	0.7%	VL003.03.02
Hardness %	91.8%	HD001.02.01
Wet Slaking %	3.4%	HD005.01.01
Dust index	2.7	PS005.02.02
Grind Distribution	-8 / +16	PS001.02.01
Sieve analysis %		
+6 mesh	0%	
-6/+12 mesh	92%	
-12/+16 mesh	7%	
-16 mesh	1%	

**Item Number:**

A45207G40: 50 lb bags, 40 bags / pallet

