

Neoprene

Commercial grade neoprene rubber (cr)

Moderate oil, acid, and abrasion resistance

Temperature range: -20 deg f to +190 deg f

Maximum pressure: 150 p.S.I.

Tensile strength: 1000 p.S.I.

Durometer: 55 to 65 shore a

Elongation: 350%

Neoprene is a good general-purpose gasketing sheet, as it will resist a wide variety of media.

For additional information please contact the sales office.

DISCLAIMER: PROPERTIES AND APPLICATION PARAMETERS SHOWN IN THIS MANUAL ARE PRESENTED IN GOOD FAITH BUT NO WARRANTY IS EXPRESSED OR IMPLIED. FAILURE TO PROPERLY USE GASKET MATERIAL COULD RESULT IN SERIOUS INJURY OR DEATH.