

## XERCAST 95 PRODUCT DATA SHEET

**XERCAST 95** is a tabular alumina based specialty castable. This material is a low iron, low-cement castable suitable for applications with service temperatures up to 3300°F.

Recommended Service Temperature	3300°F
Water Required for Mixing (as a % of weight)	5.5 - 6.0%
Material Required Per Cubic Foot	185 lbs.
Packaging	64 - 55lb bags /pallet
	1,000+lb Super Sacks

## **TYPICAL CHEMICAL ANALYSIS**

Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	CaO	Fe <sub>2</sub> O <sub>3</sub>	Alkalies
96.6	2.0	1.2	0.1	0.1

## **TYPICAL PHYSICAL PROPERTIES**

Test Temperature (°F)	Bulk Density (pcf)	C.C.S. (psi)	CMOR (psi)	Apparent Porosity (%)	Permanent Linear Change (%)
220	182 - 188	5000	1000	13 - 16	-0.1 to 0.0
1500	180 - 186	6000	1200	16 - 20	-0.3 to 0.0
2000	180 -0186	10000	2000	16 - 20	-0.3 to 0.0
2910	190 - 198	>25000	3000	10 - 14	-0.3 to 0.0

Xertech Specialties 1422 Hoelzer Ct. Dailey Industrial Park Pacific, MO 63069

Ph: (636)271-0586; Fax: (636)271-0587

www.xertechllc.com mail@xertechllc.com

Rel 11-19