



## XERGUN 2600

### PRODUCT DATA SHEET

**XERGUN 2600** is a regular cement, gunning mix for service temperatures up to 2600°F.

<b>Recommended Service Temperature</b>	<b>2600°F</b>
<b>Water Required for Mixing (as a % of weight)</b>	<b>N/A %</b>
<b>Material Required Per Cubic Foot</b>	<b>125 - 134 lbs.</b>
<b>Packaging</b>	<b>64 - 55lb bags /pallet 1,000+lb Super Sacks</b>

#### TYPICAL CHEMICAL ANALYSIS

<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>SiO<sub>2</sub></b>	<b>CaO</b>	<b>TiO<sub>2</sub></b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>
40 - 44	45 - 49	5.3 - 5.9	1.4 - 1.8	0.9 - 1.2

#### TYPICAL PHYSICAL PROPERTIES

<b>Test Temperature (°F)</b>	<b>Bulk Density (pcf)</b>	<b>C.C.S. (psi)</b>	<b>CMOR (psi)</b>	<b>Apparent Porosity (%)</b>	<b>Permanent Linear Change (%)</b>
220	128 - 136	5000	1000	----	-0.4 to 0.0
2000	120 - 130	2000	500	----	-0.5 to +0.2

Xertech Specialties  
1422 Hoelzer Ct.  
Dailey Industrial Park  
Pacific, MO 63069  
Ph: (636)271-0586; Fax: (636)271-0587

[www.xertechllc.com](http://www.xertechllc.com)  
[mail@xertechllc.com](mailto:mail@xertechllc.com)

Rel 12-14