



## XERGUN 3000

### PRODUCT DATA SHEET

**XERGUN 3000** is a reduced cement, gunning mix for service temperatures up to 3000°F.

<b>Recommended Service Temperature</b>	<b>3000°F</b>
<b>Water Required for Mixing (as a % of weight)</b>	<b>N/A %</b>
<b>Material Required Per Cubic Foot</b>	<b>131 - 138 lbs.</b>
<b>Packaging</b>	<b>64 - 55lb bags /pallet 1,000+lb Super Sacks</b>

#### TYPICAL CHEMICAL ANALYSIS

<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>SiO<sub>2</sub></b>	<b>CaO</b>	<b>TiO<sub>2</sub></b>	<b>Fe<sub>2</sub>O<sub>3</sub></b>
54 - 58	34 - 38	2.1 - 2.5	1.9 - 2.3	0.9 - 1.2

#### TYPICAL PHYSICAL PROPERTIES

<b>Test Temperature (°F)</b>	<b>Bulk Density (pcf)</b>	<b>C.C.S. (psi)</b>	<b>CMOR (psi)</b>	<b>Apparent Porosity (%)</b>	<b>Permanent Linear Change (%)</b>
220	127 - 133	1600	700	----	-0.3 to 0.0
1500	123 - 129	1200	400	----	-0.3 to 0.0
2000	122 - 128	1200	400	----	-0.5 to 0.0
2910	121 - 127	5000	1800	----	+1.3 to +2.3

Xertech Specialties  
1422 Hoelzer Ct.  
Dailey Industrial Park  
Pacific, MO 63069  
Ph: (636)271-0586; Fax: (636)271-0587

[www.xertechllc.com](http://www.xertechllc.com)  
[mail@xertechllc.com](mailto:mail@xertechllc.com)

Rel 12-14