



XERGUN 3100

PRODUCT DATA SHEET

XERGUN 3100 is a reduced cement, gunning mix for service temperatures up to 3100°F.

Recommended Service Temperature	3100°F
Water Required for Mixing (as a % of weight)	N/A %
Material Required Per Cubic Foot	147 - 154 lbs.
Packaging	64 - 55lb bags /pallet 1,000+lb Super Sacks

TYPICAL CHEMICAL ANALYSIS

Al₂O₃	SiO₂	CaO	TiO₂	Fe₂O₃
77 - 81	13 - 17	2.1 - 2.5	2.7 - 3.1	1.1 - 1.4

TYPICAL PHYSICAL PROPERTIES

Test Temperature (°F)	Bulk Density (pcf)	C.C.S. (psi)	CMOR (psi)	Apparent Porosity (%)	Permanent Linear Change (%)
220	149 - 155	2500	1000	----	-0.3 to 0.0
1500	146 - 153	2300	800	----	-0.3 to 0.0
2000	146 - 153	2300	800	----	-0.3 to +0.2
2910	136 - 143	4000	1000	----	+1.3 to +2.3

Xertech Specialties
1422 Hoelzer Ct.
Dailey Industrial Park
Pacific, MO 63069
Ph: (636)271-0586; Fax: (636)271-0587

www.xertechllc.com
mail@xertechllc.com

Rel 12-14