

## XERGUN 50

### PRODUCT DATA SHEET

**XERGUN 50** is a plastic gunning mix for service temperatures up to 3000°F.

<b>Recommended Service Temperature</b>	<b>3000°F</b>
<b>Water Required for Mixing (as a % of weight)</b>	<b>N/A %</b>
<b>Material Required Per Cubic Foot</b>	<b>125 - 130 lbs.</b>
<b>Packaging</b>	<b>64 - 55lb bags /pallet 1,000+lb Super Sacks</b>

#### TYPICAL CHEMICAL ANALYSIS

$Al_2O_3$	$SiO_2$	$CaO$	$TiO_2$	$Fe_2O_3$
48 - 52	38 - 42	1.8 - 2.2	2.1 - 2.5	1.2 - 1.6

#### TYPICAL PHYSICAL PROPERTIES

Test Temperature (°F)	Bulk Density (pcf)	C.C.S. (psi)	CMOR (psi)	Apparent Porosity (%)	Permanent Linear Change (%)
220	132 - 137	----	150	----	-0.8 to -0.3
1500	125 - 133	----	150	----	-1.0 to -0.4
2550	127 - 135	----	500	----	-0.8 to -0.4

Xertech Specialties  
1422 Hoelzer Ct.  
Dailey Industrial Park  
Pacific, MO 63069  
Ph: (636)271-0586; Fax: (636)271-0587

[www.xertechllc.com](http://www.xertechllc.com)  
[mail@xertechllc.com](mailto:mail@xertechllc.com)

Rel 12-14