



XERGUN 80

PRODUCT DATA SHEET

XERGUN 80 is a low-cement, plastic gunning mix for service temperatures up to 3200°F.

Recommended Service Temperature	3200°F
Water Required for Mixing (as a % of weight)	N/A %
Material Required Per Cubic Foot	173 - 178 lbs.
Packaging	64 - 55lb bags /pallet 1,000+lb Super Sacks

TYPICAL CHEMICAL ANALYSIS

Al₂O₃	SiO₂	CaO	TiO₂	Fe₂O₃
78 - 82	12 - 16	1.1 - 1.5	3.1 - 3.5	1.1 - 1.5

TYPICAL PHYSICAL PROPERTIES

Test Temperature (°F)	Bulk Density (pcf)	C.C.S. (psi)	CMOR (psi)	Apparent Porosity (%)	Permanent Linear Change (%)
220	162 - 168	----	400	----	-1.4 to -0.8
1500	161 - 167	----	300	----	-1.7 to -1.1
2910	150 - 157	----	1000	----	+0.3 to +1.3

Xertech Specialties
1422 Hoelzer Ct.
Dailey Industrial Park
Pacific, MO 63069
Ph: (636)271-0586; Fax: (636)271-0587

www.xertechllc.com
mail@xertechllc.com

Rel 12-14