



XERSHOT 3200

PRODUCT DATA SHEET

XERSHOT 3200 is a low-cement, shotcreting castable for service temperatures up to 3200°F.

Recommended Service Temperature	3200°F
Water Required for Mixing (as a % of weight)	5.5 – 7.5 %
Material Required Per Cubic Foot	160 - 168 lbs.
Packaging	64 - 55lb bags /pallet 1,000+lb Super Sacks

TYPICAL CHEMICAL ANALYSIS

Al_2O_3	SiO_2	CaO	TiO_2	Fe_2O_3
75 - 79	15 - 18	1.4 - 1.7	1.5 - 1.8	0.9 - 1.2

TYPICAL PHYSICAL PROPERTIES

Test Temperature (°F)	Bulk Density (pcf)	C.C.S. (psi)	CMOR (psi)	Apparent Porosity (%)	Permanent Linear Change (%)
220	162 - 167	6000	1400	11 - 14	Nil
1500	160 - 165	6000	1400	15 - 18	-0.3 to 0.0
2732	160 - 165	8000	1600	18 - 21	+0.1 to +0.5

Xertech Specialties
 1422 Hoelzer Ct.
 Dailey Industrial Park
 Pacific, MO 63069
 Ph: (636)271-0586; Fax: (636)271-0587

www.xertechllc.com
mail@xertechllc.com

Rel 12-14