# BBN Materials Co., Limited

Web: <a href="https://bbnsilicone.com">https://bbnsilicone.com</a>

Email: judy@bbnsilicone.com



## Technical Data Sheet

# Skin Safe Silicone Rubber for Sex dolls & Body Double Casting

#### 1. DESCRIPTION

BBN L8 series skin safe silicone rubber is a kind of liquid RTV-2 platinum cured mould making silicone rubber with two parts while part A is the silicone rubber and part B is the curing agent. L8 series skin safe silicone is environmental friendly, nontoxic and odorless, no side effects to human body. It is ideally for making artificial hyper-realistic adult sex toys such as silicone love dolls, silicone dildos, 3D masturbators, masturbation toys, silicone buttocks, silicone breast pads, etc.





### 2. APPEARANCE

Part A: Non-toxic and odorless liquid in translucent/skin color.

Part B: Non-toxic and odorless liquid in translucent color.

ATT: We do any curing time and any color as you requirements.

#### 3. FEATURES

- ☆ Amazing fluidity and easy to operate and de-mold
- ☆ Platinum cured (environmental, odorless and nontoxic)
- ☆ Good tear and tensile strength
- ☆ Excellent resistance to weather, temperature, acid and alkali
- ☆ Nil shrinkage rate (≤0.1%)
- $\npreceq$  High resistance to high temperature & aging (resist -60 to 250°C)

# BBN Materials Co., Limited

Web: <a href="https://bbnsilicone.com">https://bbnsilicone.com</a>

Email: judy@bbnsilicone.com



#### 4. PARAMETERS

Model No.	L800	L805	L810	L815	L820
Mixing Ratio (by weight)	1:1	1:1	1:1	1:1	1:1
Appearance/Color	Skin color				
Hardness (Shore A)	0±2	5±2	10±2	15±2	20±2
Mixed viscosity (mPa·s)	2,000±1,000	3,000±1,000	3,000±1,000	3,000±1,000	4,000±1,000
Working Time (at					
25°C/77 F, MINS)	20	20	20	20	20
Curing Time (at 25℃/77					
F, HRS)	1~2	1~2	1~2	1~2	1~2
Tensile strength, Mpa	≥1.5	≥2.0	≥2.2	≥2.3	≥2.5
Tear strength, KN/m	≥8	≥10	≥13	≥15	≥18
Elongation at break, %	≥550	≥550	≥500	≥500	≥500

Notice: We can adjust other viscosity and colors according to your needs.

#### 5. HOW TO USE

#### 1) Mixing

Dispense the parts A and B according to the ratio 1:1 by weight into a clean container and mix them thoroughly. Vacuum degassing is suggested to eliminate any entrapped air in liquid rubber.

#### 2) Pouring

Pour or inject the silicone rubber in a single spot into the sex dolls silicone molds. You can choose the one as your preference. The flow ability will decrease after mixing, pouring the material asap.

#### 3) Curing

BBN L8 series silicone rubber will cure at room temperature (25  $^{\circ}$ C). High temperature will reduce cure time, low temperature will increase the cure time or result in uncured.

#### 6. NOTICES

- 1) Read the material safety data sheet(MSDS) before use.
- 2) Keep Out Of Reach Of Children.
- 3) Use only with adequate ventilation and avoid contact with eyes. In case of eye contact flush thoroughly with water. If irritation persists gets medical attention.
- 4) Please avoid the sex dolls silicone rubber contacting or mixing with following materials in case of cure inhibition.
- $\stackrel{\leftarrow}{\sim}$  Liquid condensation silicone ( condensation silicone not completely cured or organic tin compounds ) ;
- ☆ N, P, S organic compounds;
- ☆ Ionic compounds of elements such as Sn, Pb, Hg, As, etc;
- ☆ Contains alkynes and polyvinyl compounds.

# BBN Materials Co., Limited

Web: <a href="https://bbnsilicone.com">https://bbnsilicone.com</a> Email: judy@bbnsilicone.com



## 7. PACKAGE

1) General size packages: 20kg/pail, 25kg/pail, 200kg/pail

## 8. MOLD PERFORMANCE

The physical life (duplication times) of the mold depends on how you use it (materials cast, frequency, etc). Before storing, the mold should be cleaned with a soap solution and wiped full dry.

## 9. TRANSPORTATION AND STORAGE

- 1) Sex dolls silicone rubber is non-toxic, odorless, non-flammable, noncorrosive harm, can press the non-dangerous goods and shipping.
- 2) Shelf life would be ten(10) months when stored under dry and cool place by original package under 25°C well preserved.