



Measurement	Test	Units	Target	Bleached Bag								
				30	33	35	38	40	50	60	65	70
Basis Weight	Tappi T-410	#/3,000sf	Target	30	33	35	38	40	50	60	65	70
Caliper	Tappi T-411	mils	Target	2.8	3.0	3.2	3.5	3.7	4.4	5.6	6.0	6.5
Moisture	Tappi T-412	%	Target	7%	7%	7%	7%	7%	7%	7%	7%	7%
Cobb 2 Minute	Tappi T-441	gsm	Target	32	32	32	32	32	42	42	42	42
Tear - MD	Tappi T-414	gms	Target	40	46	50	55	62	80	102	115	125
Tear - CD	Tappi T-414	gms	Target	44	52	56	62	70	90	115	130	140
Tensile - MD	Tappi T-494	#/in	Target	19	21	22	25	26	28	30	32	35
Tensile - CD	Tappi T-494	#/in	Target	7	8	9	9.5	10.5	13	16	17	18
Mullen	Tappi T-403	PSI	Target	20	22	24	26	28	35	39	42	42

*Basis weights highlighted in YELLOW show proposed specifications for products that are under development and are subject to change*

Effective: 09/10/19

Midwest Paper Group reserves the right to adjust/update product specifications at any time

Proudly Made in the USA

Virgin fiber product is compliant with both US FDA 21CFR 176.170 & 21CFR 176.180

Available with 40% PCW content US FDA CFR21 176.180 compliant only

100% Recyclable & Compostable

FSC® (C007796), SFI® (COC-6L462) and PEFC® Environmental Certifications available by request

Lacey Act compliant

### Contact Information

[customerservice@mwpaper.com](mailto:customerservice@mwpaper.com)

Phone: 888-488-6742

Hours: 7:30 am - 5:00 pm CST

Fax: 800-991-1543

540 Prospect Street

Combined Locks, WI 54113

[www.mwpaper.com](http://www.mwpaper.com)