



| Measurement              | Test       | Units                 |        | Recycled Liner |      |      |      |      |      |      |
|--------------------------|------------|-----------------------|--------|----------------|------|------|------|------|------|------|
|                          |            |                       |        | 26             | 30HP | 31HP | 35HP | 42   | 45   | 52   |
| <i>Basis Weight</i>      | Tappi T410 | #/1,000sf             | Target | 26             | 30HP | 31HP | 35HP | 42   | 45   | 52   |
| <i>Moisture</i>          | Tappi T412 | %                     | Target | 7.5%           | 7.5% | 7.5% | 7.5% | 7.5% | 7.5% | 7.5% |
| <i>STFI (CD)</i>         | Tappi T826 | lbf/in                | Target | 15             | 17   | 18   | 20   | 23   | 25   | 27   |
| <i>Porosity (Gurley)</i> | Tappi T460 | sec/100cc             | Target | 25             | 40   | 40   | 60   | 60   | 60   | 60   |
| <i>Internal Bond</i>     | Tappi T541 | ft-lb/in <sup>2</sup> | Target | 160            | 160  | 160  | 160  | 160  | 160  | 160  |
| <i>Cobb (2 Minute)</i>   | Tappi T441 | GSM                   | Target | 40             | 40   | 40   | 40   | 40   | 40   | 40   |
| <i>Slide Angle</i>       | Tappi T815 | Degrees               | Target | 20             | 20   | 20   | 20   | 20   | 20   | 20   |

Effective 09/10/19

*Midwest Paper Group reserves the right to adjust/update product specifications at any time*

Proudly Made in the USA

Product is compliant with US FDA 21CFR 176.170, 21CFR 176.180, 21CFR 176.260

100% Recyclable & Compostable

FSC® (C007796), SFI® (COC-6L462) and PEFC® Environmental Certifications available by request

Lacey Act compliant

### Contact Information

[customerservice@mwpaper.com](mailto:customerservice@mwpaper.com)

Phone: 888-488-6742

Hours: 7:30 am - 5:00 pm CST

Fax: 800-991-1543

540 Prospect Street

Combined Locks, WI 54113

[www.mwpaper.com](http://www.mwpaper.com)