



Measurement	Test	Units		Recycled Medium						
<i>Basis Weight</i>	Tappi T410	#/1,000sf	Target	18	21 HP	23	24.5 HP	26	30	33
<i>Moisture</i>	Tappi T412	%	Target	8.0%	8.0%	8.0%	8.0%	8.0%	8.0%	8.0%
<i>STFI (CD)</i>	Tappi T826	lbf/in	Target	10	13	13	14	14	16	17
<i>Concora</i>	Tappi T809	lbf	Target	42	53	53	56	56	63	65
<i>Porosity (Gurley)</i>	Tappi T460	sec/100cc	Target	20	20	20	20	20	30	30
<i>Internal Bond</i>	Tappi T541	ft-lb/in ²	Target	120	120	120	120	120	120	120
<i>Water Drop</i>	Tappi T831	Seconds	Target	5	5	5	5	5	5	5

Basis weights highlighted in YELLOW show proposed specifications for products that are under development and are subject to change.

Effective 09/10/19

Midwest Paper Group reserves the right to adjust/update product specifications at any time

Proudly Made in the USA

Product is compliant with US FDA 21CFR 176.170, 21CFR 176.180, 21CFR 176.260

100% Recyclable & Compostable

FSC® (C007796), SFI® (COC-6L462) and PEFC® Environmental Certifications available by request

Lacey Act compliant

Contact Information

customerservice@mwpaper.com

Phone: 888-488-6742

Hours: 7:30 am - 5:00 pm CST

Fax: 800-991-1543

540 Prospect Street

Combined Locks, WI 54113

www.mwpaper.com