




Construction Geosynthetics

RETAINING WALL



SG 600

STRATAGRID is geogrid reinforcement for soil. These high performance geogrids are constructed of high molecular weight and high tenacity polyester yarns utilizing a complex knitting process and polymer coating to provide superior engineering properties. Yarns are precision knitted into a dimensionally stable, uniform network of apertures providing significant tensile reinforcement capacity. STRATAGRID is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 3-9).

Property	Test Method	English	Metric
Ultimate Strength	ASTM D-6637 Method A	9,100 lbs/ft	132.8 kN/m
Tensile Strength @ 2% Strain	ASTM D-6637 Method A	870 lbs/ft	12.7 kN/m
Tensile Strength @ 5% Strain	ASTM D-6637 Method A	2,670 lbs/ft	39 kN/m
Tensile Strength @ 10% Strain	ASTM D-6637 Method A	6,090 lbs/ft	88.9 kN/m
Creep Reduction Factor		1.55	1.55
Creep Limited Strength	ASTM D-5262/D-6992	5,871 lbs/ft	85.7 kN/m
LTDS (SM, SC, CL, ML)	LTDS or Tal	4,852 lbs/ft	70.8 kN/m
LTDS (SW, SP, SM, SC)	LTDS or Tal	4,852 lbs/ft	70.8 kN/m
LTDS (GP, GW, GM, GC, SW, SP, SM, SC)	LTDS or Tal	4,641 lbs/ft	67.7 kN/m
LTDS (GP)	LTDS or Tal	4,270 lbs/ft	62.3 kN/m
LTDS (GP)(2)	LTDS or Tal	3,336 lbs/ft	48.7 kN/m
Molecular Weight (min.)	GRI GG8	25,000 g/mol	25,000 g/mol
Carboxyl End Group Count (max.)	GRI GG7	30 Meg/kg	30 Meg/kg
Aperture Size	Measured	2.45 x 0.95 in	62.2 x 24.1 mm

Reduction Factor	Value
RF(id) Soil - 25mm minus, D50 ≤ 0.2mm (SM, SC, CL, ML)	1.10
RF(id) Soil - 25mm minus, D50 ≤ 5mm (SW, SP, SM, SC)	1.10
RF(id) Soil - 25mm minus, D50 ≤ 10mm (GP, GW, GM, GC, SW, SP, SM, SC)	1.15
RF(id) Soil - 50mm minus, D50 ≤ 0.20mm (GP)	1.25
RF(id) Soil - 50mm minus, D50 ≤ 0.30mm (GP)	1.60
RF(d) (3 ≤ pH ≤ 9) (PET - CEG < 30, MW > 25,000)	1.10

Soil Interaction Coefficient	Value
Well-Graded Gravel, Sand Gravel Mix, Well-Graded Sand (SW, GW)	0.6 - 0.7
Sandy Silts & Clay (SC,GC)	0.7 - 0.8
Poorly-Graded Sand & Gravel, Silty Sand (GP, GM, SP, SM)	0.8 - 0.9
Well-Graded Gravel, Sand Gravel Mix, Well-Graded Sand (SW, GW)	0.9 - 1.0

Roll Size	Roll Diameter	Area	Weight
6' x 300'	15.5 in	200 sys	150 lbs
12' x 225'	10.0 in	300 sys	218 lbs

This information is provided for reference only and is not intended as a warranty or guarantee. US Fabrics assumes no liability in connection with the use of this information (1/2017).

US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227

Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: info@usfabrics.com