



Client Ref. : --  
Report No. : 220501ST220118(1)A

Page 1 of 2

## REPORT ON WATER ABSORPTION TEST

### Information Supplied by Client

Client : Fountain WPC Company Limited  
Project : Testing of Recycled Timber  
Sample Description : Recycle Timber

### Laboratory Information

Lab. Sample I.D. : ST220118/3-5  
Date Received : 10 March 2022  
Date Test Started : 16 March 2022  
Date Test Completed : 17 March 2022  
Test Method : ASTM D570 (24 hours)

### Test Results

Lab. Sample I.D.	Weight before water immersion (g)	Weight after 24 hours water immersion (g)	Water Absorption (%)
ST220118/3	244.597	246.292	0.69
ST220118/4	243.439	245.060	0.67
ST220118/5	244.221	245.955	0.71


Remarks : 1.) The test results relate only to the samples tested.  
2.) The results apply to the sample as received.  
3.) The test samples are shown in the photograph on page 2 of this report.  
4.) This report is to supersede our previous test report no. 220501ST220118(1).

Checked by :  Date : 26 JUL 2023 Certified by :  Date : 26 JUL 2023

Chan Chun Wai Ivan  
Manager (Product Testing Laboratory)

Client Ref. : --  
Report No. : 220501ST220118(1)A

Page 2 of 2



\*\*End of Report\*\*