

Hardline Laboratory

Report No. : HL70369/2020

Page : 1 of 2

Date : AUG. 19, 2020

UNIVERSAL MICROTECH SDN. BHD.

NO. 15, JALAN RAJA LUMU 35/132, BUKIT KEMUNING, SEKSYEN 35, 40470 SHAH ALAM, SELANGOR

The following merchandise was submitted and identified by the applicant as:

Product Description: FACE MASK MELT BLOWN FABRIC

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Requested: ASTM F2101:2019


Test Method & Result: ---See following sheet(s)---

Date of Receipt: JUL. 17, 2020

Testing Period: JUL. 17, 2020 ~ AUG. 19, 2020

Note: The ASTM F2101:2019 testing was performed by Taiwan Textile Research Institute.

Signed for and on behalf of
SGS Taiwan Ltd.


Sturm Su
Asst. Manager



Test Method & Result:

| Test Methods | Test Item | Test Results |
|---|---|--------------|
| 1. Control average: 2425 CFU 2. Mean particle size: 2.9 μm 3. Testing side: outside of specimen 4. Testing Area: 39.5 cm ² 5. Flow rate: 28.3 L/min 6. Sample Model: TFF9G496 | Bacterial Filtration Efficiency (BFE) (%) <i>Staphylococcus aureus</i> ATCC 6538 | 01 99.8 |
| | | 02 99.8 |
| | | 03 99.6 |
| | | 04 99.7 |
| | | 05 99.6 |

Note :

1. The test report merely reflects the test results of the consigned matters of the client and is not a certification
2. The content of this report is invalid if it is not presented as the entire report.

– Picture(s) –




Photo A: Appearance of the sample
- TFF9G496

---End of Report---