

A80



VERSION: 220719 Page: 1/3

SPRAY-GUN PUTTY

DEFINITION

A80 is a polyester putty applied by spray gun and especially designed for bodywork with smooth sanding, quick-drying and high levelling properties. Permits large thickness without risk of taking out.

Notable among its characteristics is its great filling capacity, which permits the irregularities on the surface to be evened out. So, it is suitable to cover founding pieces.

A80 can be applied on steel, aluminium, epoxy primers, original bodywork paints and cataphoresis, all of them previously sanded.

In case of painting on epoxy primers, it's recommended to recoat after 24h to ensure that primer is completely cured. In other case, lack of adhesion could appear.

It must not be applied over thermoplastic or nitrosynthetic paints.

It's not necessary to dilute A80. In any case, it could be diluted with 5% of polyester thinner(based in esters and styrene monomer).

A80 must be sealed with a suitable primer filler (Megax, Multyfiller Plus, ...), in order to avoid the formation of blistering, before applying the finishing coat.

PHYSICAL CHARACTERISTICS

Nature: Unsaturated polyester

Colour: Grey

Specific weight:13 lb/galat 68°FDry film thickness:400 microns2 coatsVOC:3.98 lb/galA80

1.43 lb/gal Mixing application

Solids content: 90 % Mixing application **Yield:** 163 ft²/gal 400 microns

AUXILIARY PRODUCTS

Hardener liquid for polyester

SURFACE PREPARATION

PROCESS	_	7	Steel	Aluminium	Epoxy Primers	Paint OEM	Cataphoresis
	P240		1	1	√	1	7
	DA93	↓	1	V	1	1	1

VERSION: 220719 Page: 2/3

MIXING RATIO

Hardener liquid for polyester 100:3 weight 25 min at 68°F

APPLICATION METHOD

	mm	psi	inches		<u>}</u> †/†/
> II.€	2,0 - 2,5	45	6 - 8	2	5 min 68°F
NVLP	2,0 - 2,5	30	4	2	


DRYING TIMES

68° F

140° F


Short wave IR

::::::::::::::::::::::::::::::::::::::	R		***
20 min	60 min	3 hrs	3 hrs



LAMP	FLASH	FULL
DISTANCE	OFF	BAKE
32 inches	-	

SANDING



EQUIPMENT CLEANING

Clean with a cleaning thinner before the pot life has expired

SAFETY

Follow instructions of product label. For more information check the Material Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

08A

C1

SPRAY-GUN PUTTY

VERSION: 220719 Page: 3/3

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +40°F and +90°F.

GUARANTEE

12 months in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

All clauses contained herein apply to any future changes or modifications.

For any additional technical information please consult with our Customer Service or our Technical Department.