



RESIN GLASS

B7VERSIÓN: 151026
Pag:1/2

GLASS-FIBRE PUTTY

DEFINITION

Polyester putty reinforced with fibreglass to increase its resistance. Appropriate to repair such composites as polyester parts and rusted metallic areas. Creamy putty with very easy application properties. Very good adhesion on different surfaces.

PHYSICAL CHARACTERISTICS

Nature:	Unsaturated polyester	
Colour:	Green	
Specific weight:	13.3 lb/gal @ 68°F	
VOC:	0.19 lb/gal	Mixing Application

AUXILIARY PRODUCTS

Hardener PBO

SUITABLE SURFACES


It may be applied on steel or polyester.
When maximum protection is required apply on epoxy primer.
Do not apply on thermoplastic finishes and Wash Primers.

SURFACE PREPARATION

- 1 - Identify surface.
- 2 - Process:

PROCESS		Steel	Polyester UP-GFK
	P80	✓	✓
	P150	✓	✓
	DA93	✓	✓

1 – APPLICATION

	 WEIGHT	 100	
50°F	100:2	7 min	30 min
68°F		5 min	20 min
90°F		3,5 min	15 min

2 – SANDING

 TIME	INITIAL	REVOLUTIONS	
5 min	FINAL	800 rpm	P80
 DISTANCE		 ORBIT	
32 inches		0.28-0.20 inches	P150
TMAX.			
180°F			

REMARKS

It must be isolated with a polyester putty before applying primer.
Do not add more hardener than specified. Mix thoroughly.
Polyester putties will not harden at temperatures under +40°F.

EQUIPMENT CLEANING

Clean putty knives with a cleaning thinner before the product hardens.

SAFETY

Follow instructions of product label. For more information check the Safety Data Sheets.
Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +40°F and +90°F.

GUARANTEE

In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department.
ROBERLO SA declines any responsibility due to an incorrect use of the product.