

# BT-380P Anti-Static Coating

## PRODUCT TYPE

BT-380P is translucent, blue Anti-Static Coating that provides a flexible, conductive surface on polycarbonate, PET, and other substrates.

## PROPERTIES

- Surface Resistivity of  $1 \times 10^7 - 1 \times 10^{10} \Omega/\text{cm}^2$
- Functions independent of Humidity
- High-gloss, mar-resistant finish
- Thermal Curing

## SAFETY AND EXPOSURE

All users must read and understand the Safety Data Sheet prior to using this product.

## LIQUID PROPERTIES at 25°C

| PROPERTY            | RANGE                                     |
|---------------------|---|
| Viscosity           | 10 – 20 centipoise (cP)                   |
| Specific Gravity    | 0.90 to 0.91                              |
| Solids, % by weight | 4 – 6                                     |
| pH                  | Slightly alkaline                         |
| Compatible Solvents | 1. Water<br>2. 90% Isopropanol: 10% Water |
| Maximum Dilution    | 80% Coating : 20% Solvent                 |

## CURED COATING CHARACTERISTICS

Polycarbonate substrate, 1.5 microns

| PROPERTY            | RANGE   |      |  |      |  |
|---------------------|---|------|--|------|--|
| Light Transmittance | ≥ 85% (polycarbonate); ≥ 90% (glass)  |      |  |      |  |
| Haze                | < 2.0%  |      |  |      |  |
| Adhesion            | 100% (5B)   |      |  |      |  |
| Thickness, microns  | 0.5 – 3 (1.5)   |      |  |      |  |
| Chemical Resistance | <table border="0"> <tr> <td style="vertical-align: top;">Pass</td> <td>Alcohols (ethanol/isopropanol), aliphatic (diesel/gasoline/heptane/cyclohexane), Dilute alkali</td> </tr> <tr> <td style="vertical-align: top;">Fail</td> <td>Esters (ethyl acetate), Ketones (acetone, 2-heptanone; 2-butanone), Concentrated/Dilute acid &amp; alkali, Dichloromethane</td> </tr> </table> | Pass | Alcohols (ethanol/isopropanol), aliphatic (diesel/gasoline/heptane/cyclohexane), Dilute alkali | Fail | Esters (ethyl acetate), Ketones (acetone, 2-heptanone; 2-butanone), Concentrated/Dilute acid & alkali, Dichloromethane |
| Pass                | Alcohols (ethanol/isopropanol), aliphatic (diesel/gasoline/heptane/cyclohexane), Dilute alkali  |      |  |      |  |
| Fail                | Esters (ethyl acetate), Ketones (acetone, 2-heptanone; 2-butanone), Concentrated/Dilute acid & alkali, Dichloromethane  |      |  |      |  |

## WARRANTY LIMITATIONS

The physical and performance properties cited herein represent typical values for BT-380P Anti-Static Coating, and are not meant as exact specifications. Customers must conduct their own validation testing to determine the appropriate use of this product for any purpose. This information is not to be considered a warranty or license to infringe upon any patented process or product; no liability for infringement arising out of such a use is assumed.

## DELIVERY OPTIONS

The BT-380P Anti-Static Coating solution is available for shipment within two weeks of order confirmation, and is available in quart, gallon, five-gallon pail, and 55-gallon drum containers. Contact Exxene to select the best payment option and the optimum shipping method according to your preference and region. All charges, duties, and fees associated with the shipment and its contents are the responsibility of the customer.

## APPLICATION PARAMETERS

| PROPERTY   | RANGE  |
|--|--|
| Application Method<br>Dip<br>Spray<br>Flow Coat  | 2 – 3 mm /second withdrawal rate<br>15 – 30 psi HVLP; fine tip<br>As appropriate to flow system  |
| Environment<br>Temperature/Humidity<br>Dew point | 16 – 27°C / 20 – 45 % RH<br>Dew point must be at least 5° lower than room temperature.   |
| Air quality                                      | Laminar, top-down flow < 5 cfm<br>Particle count as appropriate ( ≤ Class 10,000 )   |
| Coating Temperature                              | Within 5° of Ambient temperature   |
| Coating Filtration                               | Polyethylene or polypropylene; nominal media rated at 1.0 to 5.0 microns as a pre-filter; absolute media rated at 5.0 to 10.0 microns. <i>Filter before every use.</i> |
| Cure Conditions                                  | 40 – 60 minutes at 60°C<br>20 – 40 minutes at 120°C  |

## EQUIPMENT PREPARATION

**Compatible Materials:** All equipment surfaces must be constructed of stainless steel, polyethylene, polypropylene or similar, chemical resistance substances. Mild steel, brass, copper, and polyvinyl chloride (PVC) or plasticizer-containing materials cannot be allowed to contact the coating solution.

**Cleaning:** All coating equipment must be thoroughly cleaned with a compatible solvent to remove all traces of other coatings, solvents, or old batches of the same product. After all residues have been removed from the equipment, multiple rinses of water or a premixed solution of 90% Isopropanol and 10% water are used to prepare the system for the introduction of filtered BT-380P Anti-Static Coating solution. Dried Anti-Static Coating residue may be removed with an aqueous 10 – 20% solution of sodium or potassium hydroxide.

**STORAGE** BT-380P solution is stored at room temperature, or at refrigerated temperatures above 5 °C. Do not freeze. When stored in the original, sealed container, the solution should be used within three months.

**SUPPORT** Contact Us via telephone at +1(361) 991-8391, email [Info@Exxene.com](mailto:Info@Exxene.com), or fax to +1(361) 991-9057. We are located at 5939 Holly Road, Corpus Christi, TX 78414.